



US009125739B2

(12) **United States Patent**
Paniagua et al.

(10) **Patent No.:** **US 9,125,739 B2**
(45) **Date of Patent:** **Sep. 8, 2015**

(54) **PERCUTANEOUS REPLACEMENT HEART VALVE AND A DELIVERY AND IMPLANTATION SYSTEM**

(71) Applicant: **Colibri Heart Valve LLC**, Broomfield, CO (US)

(72) Inventors: **David Paniagua**, Houston, TX (US); **R. David Fish**, Houston, TX (US)

(73) Assignee: **COLIBRI HEART VALVE LLC**, Broomfield, CO (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/253,650**

(22) Filed: **Apr. 15, 2014**

(65) **Prior Publication Data**

US 2014/0228944 A1 Aug. 14, 2014

Related U.S. Application Data

(63) Continuation of application No. 13/675,665, filed on Nov. 13, 2012, which is a continuation of application No. 10/887,688, filed on Jul. 10, 2004, now Pat. No. 8,308,797, which is a continuation-in-part of application No. 10/037,266, filed on Jan. 4, 2002, now abandoned.

(51) **Int. Cl.**
A61F 2/24 (2006.01)
A61B 8/12 (2006.01)
A61F 2/95 (2013.01)

(52) **U.S. Cl.**
CPC **A61F 2/2412** (2013.01); **A61B 8/12** (2013.01); **A61F 2/24** (2013.01); **A61F 2/2415** (2013.01); **A61F 2/2418** (2013.01); **A61F 2/2427** (2013.01); **A61F 2/2433** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC A61F 2/2412; A61F 2/2436

USPC 623/1.24, 1.26, 2.12–2.19

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,014,024 A 12/1961 Lieberman et al.

3,029,819 A 4/1962 Edward

(Continued)

FOREIGN PATENT DOCUMENTS

EP 1603493 12/2005

EP 2000115 5/2011

(Continued)

OTHER PUBLICATIONS

Cross-reference is made to U.S. Appl. No. 14/253,656, filed Apr. 15, 2014, and its associated Preliminary Amendment.

(Continued)

Primary Examiner — Thomas J Sweet


Assistant Examiner — Cheryl Miller

(74) *Attorney, Agent, or Firm* — Fox Rothschild LLP

(57) **ABSTRACT**

A method of making a replacement heart valve device whereby a fragment of biocompatible tissue material is treated and soaked in one or more alcohol solutions and a solution of glutaraldehyde. The dried biocompatible tissue material is folded and rehydrated in such a way that forms a two- or three-leaflet/cusp valve without affixing of separate cusps or leaflets or cutting slits into the biocompatible tissue material to form the cusps or leaflets. After the biocompatible tissue material is folded, it is affixed at one or more points on the outer surface to the inner cavity or a stent.

5 Claims, 12 Drawing Sheets



(52) U.S. Cl.

CPC *A61F2/2436* (2013.01); *A61F 2/2475*
 (2013.01); *A61F 2/2439* (2013.01); *A61F*
2002/9534 (2013.01); *A61F 2210/0014*
 (2013.01); *A61F 2220/0008* (2013.01); *A61F*
2220/0016 (2013.01); *A61F 2220/0075*
 (2013.01); *A61F 2230/0078* (2013.01); *A61F*
2250/0039 (2013.01); *Y10S 623/917* (2013.01);
Y10T 29/49412 (2015.01)

(56)

References Cited

U.S. PATENT DOCUMENTS

3,105,492 A	10/1963	Jeckel	5,047,050 A	9/1991	Arpesani
3,320,972 A	5/1967	High et al.	5,052,771 A	10/1991	Williams et al.
3,409,914 A	11/1968	Jones	5,061,277 A	10/1991	Carpentier et al.
3,548,417 A	12/1970	Kischer et al.	5,080,660 A	1/1992	Buelna
3,562,820 A	2/1971	Braun	5,139,515 A	8/1992	Robicsek
3,588,920 A	6/1971	Wesolowski	5,163,955 A	11/1992	Love et al.
3,671,979 A	6/1972	Moulopoulos	5,171,273 A	12/1992	Silver et al.
3,709,175 A	1/1973	Edwards et al.	5,226,889 A	7/1993	Sheiban
3,878,565 A	4/1975	Sauvage	5,261,878 A	11/1993	Galindo
3,945,052 A	3/1976	Liebig	5,282,847 A	2/1994	Trescony et al.
3,966,401 A	6/1976	Hancock et al.	5,326,370 A	7/1994	Love et al.
3,983,581 A	10/1976	Angell et al.	5,326,371 A	7/1994	Love et al.
3,986,828 A	10/1976	Hoffman, Jr. et al.	5,332,402 A	7/1994	Teitelbaum
4,011,947 A	3/1977	Sawyer	5,336,616 A	8/1994	Livesey et al.
4,035,849 A	7/1977	Angell et al.	5,360,443 A	11/1994	Barone et al.
4,055,861 A	11/1977	Carpentier et al.	5,374,539 A	12/1994	Nimni et al.
4,056,854 A	11/1977	Boretos et al.	5,376,110 A	12/1994	Tu et al.
4,060,081 A	11/1977	Yannas et al.	5,383,927 A	1/1995	De Goicochea et al.
4,082,507 A	4/1978	Sawyer	5,411,552 A	5/1995	Andersen et al.
4,084,268 A	4/1978	Ionescu et al.	5,413,601 A	5/1995	Keshelava
4,106,129 A	8/1978	Carpentier et al.	5,449,384 A	9/1995	Johnson
4,164,045 A	8/1979	Bokros et al.	5,476,506 A	12/1995	Lunn
4,172,295 A	10/1979	Batten	5,480,424 A	1/1996	Cox
4,218,782 A	8/1980	Rygg	5,484,444 A	1/1996	Braunschweiler et al.
4,222,126 A	9/1980	Boretos et al.	5,489,297 A	2/1996	Duran
4,233,493 A	11/1980	Nath et al.	5,500,015 A	3/1996	Deac
4,265,694 A	5/1981	Boretos et al.	5,509,930 A	4/1996	Love
4,291,420 A	9/1981	Reul	5,522,879 A	6/1996	Scopelianos
4,340,977 A	7/1982	Brownlee et al.	5,522,881 A	6/1996	Lentz
4,350,492 A	9/1982	Wright et al.	5,545,215 A	8/1996	Duran
4,364,127 A	12/1982	Pierce et al.	5,549,664 A	8/1996	Hirata et al.
4,388,735 A	6/1983	Ionescu et al.	5,549,666 A	8/1996	Hata et al.
4,423,525 A	1/1984	Vallana et al.	5,554,184 A	9/1996	Machiraju
4,441,216 A	4/1984	Ionescu et al.	5,571,170 A	11/1996	Palmas et al.
4,456,589 A	6/1984	Holman et al.	5,571,173 A	11/1996	Parodi
4,473,423 A	9/1984	Kolff	5,571,174 A	11/1996	Love et al.
4,477,930 A	10/1984	Totten et al.	5,578,071 A	11/1996	Parodi
4,490,859 A	1/1985	Black et al.	5,578,072 A	11/1996	Barone et al.
4,517,687 A	5/1985	Liebig et al.	5,582,168 A	12/1996	Samuels et al.
4,545,082 A	10/1985	Hood	5,591,229 A	1/1997	Parodi
4,597,762 A	7/1986	Walter et al.	5,634,928 A	6/1997	Fischell et al.
4,600,533 A	7/1986	Chu	5,645,559 A	7/1997	Hachtman et al.
4,631,052 A	12/1986	Kensey	5,653,749 A	8/1997	Love et al.
4,657,133 A	4/1987	Komatsu et al.	5,683,451 A	11/1997	Lenker et al.
4,666,442 A	5/1987	Arru et al.	5,713,953 A	2/1998	Vallana et al.
4,728,328 A	3/1988	Hughes et al.	5,728,152 A	3/1998	Mirsch, II et al.
4,743,231 A	5/1988	Kay et al.	5,733,299 A	3/1998	Sheiban et al.
4,759,758 A	7/1988	Gabbay	5,741,333 A	4/1998	Frid
4,759,759 A	7/1988	Walker et al.	5,746,775 A	5/1998	Levy et al.
4,798,611 A	1/1989	Freeman, Jr.	5,769,780 A	6/1998	Hata et al.
4,801,299 A	1/1989	Brendel et al.	5,782,914 A	7/1998	Schankereli
4,870,966 A	10/1989	Dellon et al.	5,787,887 A	8/1998	Klingenbeck-Regn
4,883,458 A	11/1989	Shiber	5,840,081 A	11/1998	Andersen et al.
4,892,539 A	1/1990	Koch	5,855,601 A	1/1999	Bessler et al.
4,966,604 A	10/1990	Reiss	5,861,028 A	1/1999	Angell
4,976,733 A	12/1990	Giradot	5,862,806 A	1/1999	Cheung
4,979,939 A	12/1990	Shiber	5,876,448 A	3/1999	Thompson et al.
5,006,104 A	4/1991	Smith et al.	5,895,420 A	4/1999	Mirsch, II et al.
5,007,896 A	4/1991	Shiber	5,931,969 A	8/1999	Carpentier et al.
5,011,488 A	4/1991	Ginsburg	5,957,949 A	9/1999	Leonhardt et al.
5,026,366 A	6/1991	Leckrone	5,961,539 A	10/1999	Northup et al.
5,032,128 A	7/1991	Alonso	5,961,549 A	10/1999	Nguyen et al.
5,047,041 A	9/1991	Samuels	5,972,030 A	10/1999	Garrison et al.
			5,976,179 A	11/1999	Inoue
			6,004,328 A	12/1999	Solar
			6,004,330 A	12/1999	Middleman et al.
			6,010,531 A	1/2000	Donlon et al.
			6,029,671 A	2/2000	Stevens et al.
			6,045,576 A	4/2000	Starr et al.
			6,053,938 A	4/2000	Goldmann et al.
			6,091,984 A	7/2000	Perelman et al.
			6,102,944 A	8/2000	Huynh et al.
			6,117,169 A	9/2000	Moe
			6,124,523 A	9/2000	Banas et al.
			6,125,852 A	10/2000	Stevens et al.
			6,126,686 A	10/2000	Badylak et al.
			6,129,756 A	10/2000	Kugler
			6,162,245 A	12/2000	Jayaraman
			6,168,614 B1	1/2001	Andersen et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

6,168,619	B1	1/2001	Dinh et al.	6,736,823	B2	5/2004	Darios et al.
6,171,335	B1	1/2001	Wheatley et al.	6,764,510	B2	7/2004	Vidlund et al.
6,174,327	B1	1/2001	Mertens et al.	6,773,456	B1	8/2004	Gordon et al.
6,186,999	B1	2/2001	Chen	6,773,457	B2	8/2004	Ivancev
6,197,143	B1	3/2001	Bodnar	6,790,229	B1	9/2004	Berrekouw
6,214,055	B1	4/2001	Simionescu et al.	6,792,979	B2	9/2004	Konya et al.
6,221,091	B1	4/2001	Khosravi	6,802,319	B2	10/2004	Stevens et al.
6,231,602	B1	5/2001	Carpentier et al.	6,802,806	B2	10/2004	McCarthy et al.
6,245,102	B1	6/2001	Jayaraman	6,821,297	B2	11/2004	Snyders
6,254,629	B1	7/2001	Inoue	6,821,530	B2	11/2004	Koob et al.
6,254,630	B1	7/2001	Inoue	6,830,584	B1	12/2004	Seguin
6,254,636	B1	7/2001	Peredo	6,893,460	B2	5/2005	Spenser et al.
6,264,691	B1	7/2001	Gabbay	6,896,690	B1	5/2005	Lambrecht et al.
6,269,819	B1	8/2001	Oz et al.	6,908,481	B2 *	6/2005	Cribier 623/2.11
6,270,526	B1	8/2001	Cox	6,913,608	B2	7/2005	Liddicoat et al.
6,277,397	B1	8/2001	Shimizu	6,916,338	B2	7/2005	Speziali
6,277,555	B1	8/2001	Duran et al.	6,942,694	B2	9/2005	Liddicoat et al.
6,287,335	B1	9/2001	Drasler et al.	6,951,571	B1	10/2005	Srivastava
6,293,970	B1	9/2001	Wolfenbarger, Jr. et al.	6,961,123	B1	11/2005	Wang et al.
6,312,462	B1	11/2001	McDermott et al.	6,977,231	B1	12/2005	Matsuda
6,312,474	B1	11/2001	Francis et al.	6,986,735	B2	1/2006	Abraham et al.
6,334,873	B1	1/2002	Lane et al.	7,004,925	B2	2/2006	Navia et al.
6,342,069	B1	1/2002	Deac et al.	7,008,763	B2	3/2006	Cheung
6,350,278	B1	2/2002	Lenker et al.	7,011,688	B2	3/2006	Gryska et al.
6,350,282	B1	2/2002	Eberhardt	7,018,404	B2	3/2006	Holmberg et al.
6,352,554	B2	3/2002	De Paulis	7,018,406	B2	3/2006	Seguin et al.
6,352,708	B1	3/2002	Duran et al.	7,022,348	B2	4/2006	Ketharanathan
6,358,275	B1	3/2002	McIlroy et al.	7,025,780	B2	4/2006	Gabbay
6,358,284	B1	3/2002	Fearnot et al.	7,037,333	B2	5/2006	Myers et al.
6,371,980	B1	4/2002	Rudakov et al.	7,039,446	B2	5/2006	Ruchti et al.
6,376,244	B1	4/2002	Atala et al.	7,041,132	B2	5/2006	Quijano et al.
6,378,221	B1	4/2002	Ekholm, Jr. et al.	7,053,051	B2	5/2006	Hendriks et al.
6,383,171	B1	5/2002	Gifford et al.	7,060,092	B2	6/2006	Kuribayashi et al.
6,391,333	B1	5/2002	Li et al.	7,070,616	B2	7/2006	Majercak et al.
6,409,755	B1	6/2002	Vrba	7,077,862	B2	7/2006	Vidlund et al.
6,418,339	B1	7/2002	Essenpreis et al.	7,084,082	B1	8/2006	Shimizu
6,425,916	B1 *	7/2002	Garrison et al. 623/2.11	7,138,226	B2	11/2006	Vincek et al.
6,432,712	B1	8/2002	Wolfenbarger, Jr. et al.	7,153,324	B2	12/2006	Case et al.
6,440,167	B2	8/2002	Shimizu	7,160,322	B2	1/2007	Gabbay
6,458,153	B1	10/2002	Bailey et al.	7,164,145	B2	1/2007	Shakespeare
6,461,382	B1	10/2002	Cao	7,166,570	B2	1/2007	Hunter et al.
6,468,313	B1	10/2002	Claeson et al.	7,189,259	B2	3/2007	Simionescu et al.
6,471,723	B1	10/2002	Ashworth et al.	7,213,601	B2	5/2007	Stevens et al.
6,482,227	B1	11/2002	Solovay	7,214,242	B2	5/2007	Abraham et al.
6,482,228	B1	11/2002	Norred	7,232,461	B2	6/2007	Ramer
6,482,240	B1	11/2002	Echmayer et al.	7,261,732	B2	8/2007	Justino
6,491,719	B1	12/2002	Fogarty et al.	7,289,211	B1	10/2007	Walsh, Jr. et al.
6,494,909	B2	12/2002	Greenhalgh	7,309,461	B2	12/2007	Kujawski et al.
6,503,272	B2	1/2003	Duerig et al.	7,311,730	B2	12/2007	Gabbay
6,530,952	B2	3/2003	Vesely	7,318,998	B2	1/2008	Goldstein et al.
6,534,004	B2	3/2003	Chen et al.	7,329,279	B2	2/2008	Haug et al.
6,540,782	B1	4/2003	Snyders	7,331,993	B2	2/2008	White
6,553,681	B2	4/2003	Ekholm, Jr. et al.	7,354,702	B2	4/2008	Dai et al.
6,558,418	B2	5/2003	Carpentier et al.	RE40,404	E	6/2008	Schmitt et al.
6,565,960	B2	5/2003	Koob et al.	7,381,218	B2	6/2008	Schreck
6,569,200	B2	5/2003	Wolfenbarger, Jr. et al.	7,381,219	B2	6/2008	Salahieh et al.
6,582,458	B1	6/2003	White et al.	7,399,315	B2	7/2008	Iobbi
6,582,462	B1	6/2003	Andersen et al.	7,427,291	B2	9/2008	Liddicoat et al.
6,582,464	B2	6/2003	Gabbay	7,431,725	B2	10/2008	Stack et al.
6,599,524	B2	7/2003	Li et al.	7,468,073	B2	12/2008	Johnson et al.
6,610,088	B1	8/2003	Gabbay	7,473,237	B2	1/2009	Navia et al.
6,624,890	B2	9/2003	Backman et al.	7,481,838	B2	1/2009	Carpentier et al.
6,626,938	B1	9/2003	Butaric et al.	7,503,929	B2	3/2009	Johnson et al.
6,652,577	B2	11/2003	Gianotti	7,510,571	B2	3/2009	Spiridigliozzi et al.
6,652,578	B2 *	11/2003	Bailey et al. 623/1.24	7,510,575	B2	3/2009	Spenser et al.
6,666,886	B1	12/2003	Tranquillo et al.	7,524,330	B2	4/2009	Berrekouw
6,676,698	B2	1/2004	McGuckin, Jr.	7,556,646	B2 *	7/2009	Yang et al. 623/2.11
6,682,537	B2	1/2004	Ouriel et al.	7,566,343	B2	7/2009	Jenson et al.
6,682,559	B2	1/2004	Myers et al.	7,585,321	B2	9/2009	Cribier
6,685,739	B2	2/2004	Dimatteo et al.	7,604,661	B2	10/2009	Pavcnik et al.
6,696,074	B2	2/2004	Dia et al.	7,618,446	B2	11/2009	Andersen et al.
6,702,826	B2	3/2004	Liddicoat et al.	7,622,276	B2	11/2009	Cunanan et al.
6,719,788	B2	4/2004	Cox	7,628,805	B2	12/2009	Spenser et al.
6,719,789	B2	4/2004	Cox	7,648,676	B2	1/2010	Mills et al.
6,733,525	B2	5/2004	Yang et al.	7,670,368	B2	3/2010	Hill et al.
				7,708,775	B2	5/2010	Rowe et al.
				7,758,632	B2	7/2010	Hojeibane et al.
				7,780,722	B2	8/2010	Thielen et al.
				7,789,909	B2	9/2010	Andersen et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

7,846,203	B2	12/2010	Cribier	2005/0228494	A1	10/2005	Marquez
7,846,204	B2	12/2010	Letac et al.	2005/0241981	A1	11/2005	Gupta et al.
7,871,431	B2	1/2011	Gurm et al.	2005/0246035	A1	11/2005	Wolfenbarger et al.
7,892,281	B2	2/2011	Seguin et al.	2005/0247320	A1	11/2005	Stack et al.
7,914,576	B2	3/2011	Navia et al.	2005/0267529	A1	12/2005	Crockett et al.
RE42,395	E	5/2011	Wright et al.	2006/0004439	A1	1/2006	Spenser et al.
7,967,833	B2	6/2011	Sterman et al.	2006/0004443	A1	1/2006	Liddicoat et al.
7,981,151	B2	7/2011	Rowe	2006/0020336	A1	1/2006	Liddicoat
8,002,825	B2	8/2011	Letac et al.	2006/0025800	A1	2/2006	Suresh
8,007,992	B2	8/2011	Tian et al.	2006/0041306	A1	2/2006	Vidlund
8,057,540	B2	11/2011	Letac et al.	2006/0074486	A1	4/2006	Liddicoat et al.
8,080,054	B2	12/2011	Rowe	2006/0089708	A1	4/2006	Osse et al.
8,105,375	B2	1/2012	Navia et al.	2006/0111733	A1	5/2006	Shriver
8,512,401	B2	8/2013	Murray et al.	2006/0129225	A1	6/2006	Kopia et al.
8,512,403	B2	8/2013	Navia et al.	2006/0134079	A1	6/2006	Sih et al.
2001/0010017	A1	7/2001	Cribier et al.	2006/0140916	A1	6/2006	Siani-Rose et al.
2001/0023372	A1	9/2001	Chen et al.	2006/0173475	A1	8/2006	Lafontaine et al.
2001/0049558	A1	12/2001	Liddicoat et al.	2006/0178740	A1	8/2006	Stacchino et al.
2002/0005073	A1	1/2002	Tompkins et al.	2006/0190074	A1	8/2006	Hill et al.
2002/0028243	A1	3/2002	Masters	2006/0193885	A1	8/2006	Neethling et al.
2002/0029783	A1	3/2002	Stevens et al.	2006/0195010	A1	8/2006	Arnal et al.
2002/0032481	A1*	3/2002	Gabbay 623/2.11	2006/0195183	A1	8/2006	Navia et al.
2002/0037940	A1	3/2002	Koob et al.	2006/0206203	A1	9/2006	Yang et al.
2002/0042621	A1	4/2002	Liddicoat et al.	2006/0229701	A1	10/2006	Gurm et al.
2002/0052651	A1	5/2002	Myers et al.	2006/0240063	A9	10/2006	Hunter et al.
2002/0091441	A1	7/2002	Guzik	2006/0240064	A9	10/2006	Hunter et al.
2002/0095167	A1	7/2002	Liddicoat et al.	2006/0259134	A1	11/2006	Schwammenthal et al.
2002/0095994	A1	7/2002	Vesley et al.	2006/0259135	A1	11/2006	Navia et al.
2002/0123789	A1	9/2002	Francis et al.	2006/0259137	A1	11/2006	Artof et al.
2002/0128708	A1	9/2002	Northrup et al.	2006/0265056	A1	11/2006	Nguyen et al.
2002/0151970	A1	10/2002	Garrison et al.	2006/0287571	A1	12/2006	Gozzi et al.
2003/0027332	A1	2/2003	Lafrance et al.	2006/0292125	A1	12/2006	Kellar et al.
2003/0078659	A1	4/2003	Yang	2007/0010857	A1	1/2007	Sugimoto et al.
2003/0102000	A1	6/2003	Stevens et al.	2007/0043431	A1	2/2007	Melsheimer
2003/0130727	A1	7/2003	Drasler et al.	2007/0050014	A1	3/2007	Johnson
2003/0130729	A1	7/2003	Paniagua et al.	2007/0050022	A1	3/2007	Vidlund et al.
2003/0130731	A1	7/2003	Vidlund et al.	2007/0056346	A1	3/2007	Spenser et al.
2003/0149477	A1	8/2003	Gabbay	2007/0060932	A1	3/2007	Stack et al.
2003/0153974	A1	8/2003	Spenser et al.	2007/0061008	A1	3/2007	Salahieh et al.
2003/0187362	A1	10/2003	Murphy et al.	2007/0100426	A1	5/2007	Rudakov et al.
2003/0195620	A1	10/2003	Huynh et al.	2007/0104395	A1	5/2007	Kinigakis et al.
2003/0204023	A1	10/2003	Koob et al.	2007/0128174	A1	6/2007	Kleinsek et al.
2003/0209835	A1	11/2003	Chun et al.	2007/0173861	A1	7/2007	Strommer et al.
2003/0212460	A1	11/2003	Darios et al.	2007/0203575	A1	8/2007	Forster et al.
2003/0212462	A1	11/2003	Gryska et al.	2007/0213813	A1	9/2007	Von Segesser et al.
2003/0217415	A1	11/2003	Crouch et al.	2007/0250154	A1	10/2007	Greenberg et al.
2004/0024452	A1	2/2004	Kruse et al.	2007/0263226	A1	11/2007	Kurtz et al.
2004/0039442	A1	2/2004	St. Goar	2007/0276432	A1	11/2007	Stack et al.
2004/0055608	A1	3/2004	Stevens et al.	2007/0276461	A1	11/2007	Andreas et al.
2004/0059418	A1	3/2004	McKay et al.	2008/0004686	A1	1/2008	Hunt et al.
2004/0098092	A1	5/2004	Butaric et al.	2008/0009667	A1	1/2008	Longhini et al.
2004/0158321	A1	8/2004	Reuter et al.	2008/0009940	A1	1/2008	Cribier
2004/0193261	A1	9/2004	Berrekouw	2008/0029105	A1	2/2008	Stevens et al.
2004/0230285	A1	11/2004	Gifford, III et al.	2008/0039871	A1	2/2008	Wallace et al.
2004/0243153	A1	12/2004	Liddicoat et al.	2008/0039926	A1	2/2008	Majercak et al.
2004/0243229	A1	12/2004	Vidlund et al.	2008/0058798	A1	3/2008	Wallace et al.
2005/0004668	A1	1/2005	Aklog et al.	2008/0082113	A1	4/2008	Bishop et al.
2005/0027369	A1	2/2005	Eldridge et al.	2008/0102439	A1	5/2008	Tian et al.
2005/0043819	A1	2/2005	Schmidt et al.	2008/0133004	A1	6/2008	White
2005/0096673	A1	5/2005	Stack et al.	2008/0147182	A1	6/2008	Righini et al.
2005/0113910	A1	5/2005	Paniagua et al.	2008/0154356	A1	6/2008	Obermiller et al.
2005/0137681	A1	6/2005	Shoemaker et al.	2008/0177381	A1	7/2008	Navia et al.
2005/0137682	A1	6/2005	Justino	2008/0183280	A1	7/2008	Agnew et al.
2005/0142163	A1	6/2005	Hunter et al.	2008/0183283	A1	7/2008	Downing
2005/0147562	A1	7/2005	Hunter et al.	2008/0190989	A1	8/2008	Crews et al.
2005/0147599	A1	7/2005	Hunter et al.	2008/0195200	A1	8/2008	Vidlund et al.
2005/0147643	A1	7/2005	Hunter et al.	2008/0199843	A1	8/2008	Haverich et al.
2005/0148512	A1	7/2005	Hunter et al.	2008/0200977	A1	8/2008	Paul et al.
2005/0158274	A1	7/2005	Hunter et al.	2009/0005857	A1	1/2009	Ischinger
2005/0159811	A1	7/2005	Lane	2009/0030511	A1	1/2009	Paniagua et al.
2005/0169958	A1	8/2005	Hunter et al.	2009/0043383	A1	2/2009	McGregor et al.
2005/0169959	A1	8/2005	Hunter et al.	2009/0054969	A1	2/2009	Salahieh
2005/0175657	A1	8/2005	Hunter et al.	2009/0062907	A1	3/2009	Quijano et al.
2005/0187618	A1	8/2005	Gabbay	2009/0112309	A1	4/2009	Jaramillo et al.
2005/0191248	A1	9/2005	Hunter et al.	2009/0132032	A9	5/2009	Cribier
				2009/0157175	A1	6/2009	Benichou
				2009/0164005	A1	6/2009	Dove et al.
				2009/0187241	A1	7/2009	Melsheimer
				2009/0248149	A1	10/2009	Gabbay

(56) **References Cited**
U.S. PATENT DOCUMENTS

2009/0254175 A1 10/2009 Quijano et al.
 2009/0281609 A1 11/2009 Benichou et al.
 2010/0030259 A1 2/2010 Pavcnik et al.
 2010/0036479 A1 2/2010 Hill et al.
 2010/0036484 A1 2/2010 Hariton et al.
 2010/0043197 A1 2/2010 Abbate et al.
 2010/0048987 A1 2/2010 Khairkahan
 2010/0049312 A1 2/2010 Edoga et al.
 2010/0131054 A1 5/2010 Tuval et al.
 2010/0161036 A1 6/2010 Pintor et al.
 2010/0185277 A1 7/2010 Braidio et al.
 2010/0217382 A1 8/2010 Chau et al.
 2010/0234878 A1 9/2010 Hruska
 2010/0241069 A1 9/2010 Hatten
 2010/0249918 A1 9/2010 Zhang
 2010/0256749 A1 10/2010 Tran et al.
 2010/0256751 A1 10/2010 Rowe et al.
 2010/0312333 A1 12/2010 Navia et al.
 2011/0004299 A1 1/2011 Navia et al.
 2011/0015728 A1 1/2011 Jimenez et al.
 2011/0040375 A1 2/2011 Letac et al.
 2011/0087322 A1 4/2011 Letac et al.
 2011/0137409 A1 6/2011 Yang et al.
 2011/0146361 A1 6/2011 Davidson et al.
 2011/0153009 A1 6/2011 Navia et al.
 2011/0166636 A1 7/2011 Rowe
 2011/0178597 A9 7/2011 Navia et al.
 2011/0218619 A1 9/2011 Benichou et al.
 2011/0224607 A1 9/2011 Vogelbaum et al.
 2011/0240511 A1 10/2011 Bolton et al.
 2011/0300625 A1 12/2011 Paniagua et al.
 2011/0301700 A1 12/2011 Fish et al.
 2012/0078343 A1 3/2012 Fish
 2012/0078356 A1 3/2012 Fish et al.
 2012/0095551 A1 4/2012 Navia et al.
 2012/0158128 A1 6/2012 Gautam et al.
 2012/0185038 A1 7/2012 Fish et al.
 2012/0310041 A1 12/2012 Paniagua et al.
 2014/0039613 A1 2/2013 Navia et al.
 2013/0304201 A1 11/2013 Navia et al.

FOREIGN PATENT DOCUMENTS

EP 1441672 9/2011
 EP 2055266 2/2012
 EP 1621162 5/2012
 EP 2260796 2/2013
 JP 9-501594 2/1997
 JP 2001-500761 1/2001
 JP 2005-103321 4/2005
 RU 2355361 C 5/2009
 WO 91/17720 11/1991
 WO 92/17118 10/1992
 WO 98/29057 7/1998
 WO 99/30646 6/1999
 WO 00/12164 3/2000
 WO 01/02031 1/2001
 WO 03/047468 6/2003
 WO 03/092554 11/2003
 WO 2004/026124 4/2004
 WO 2004/082527 9/2004
 WO 2006/095342 9/2006
 WO 2007/138572 12/2007
 WO 2008/063537 8/2008
 WO 2008/106531 9/2008
 WO 2009/052188 4/2009
 WO 2009/149462 12/2009
 WO 2009/156471 12/2009
 WO 2010/024801 3/2010
 WO 2010/027363 3/2010
 WO 2010/080594 7/2010
 WO 2010/117541 10/2010
 WO 2011/109433 3/2011
 WO 2011/109450 9/2011

WO 2012/006124 1/2012
 WO 2012/040643 3/2012
 WO 2012/082952 6/2012

OTHER PUBLICATIONS

Cross-reference is made to U.S. Appl. No. 14/268,184, filed May 2, 2014, and its associated Preliminary Amendment.
 Cross-reference is made to U.S. Appl. No. 14/268,190, filed May 2, 2014, and its associated Preliminary Amendment.
 Cross-reference is made to U.S. Appl. No. 14/284,049, filed May 21, 2014, and its associated Preliminary Amendment.
 Cross-reference is made to U.S. Appl. No. 14/284,063, filed May 21, 2014, and its associated Preliminary Amendment.
 Paniagua, David et al., Abstract 4622: "Percutaneous Implantation of a Low Profile, Dry Membrane, Heart Valve in an Integrated Delivery System in the Aortic and Pulmonary Positions: One-month Animal Results," Circulation, American Heart Association, Inc., 2009; vol. 120: pp. 982.
 Pathak, CP et al., "Treatment of bioprosthetic heart valve tissue with long chain alcohol solution to lower calcification potential" J Biomed Mater Res A. Apr. 1, 2004;69(1), pp. 140-144.
 Pavenik, Susan, M.D., PhD et al., "Development and Initial Experimental Evaluation of a Prosthetic Aortic Valve for Transcatheter Placement" Cardiovascular Radiology, Apr. 1992, pp. 151-154.
 Pick, Adam, "True or False: An Edwards Lifesciences' Tissue Valve Replacement Requires 1,800 Hand-Sewn Stitches" <http://heart-valve-surgery.com/heart-surgery-blog/2008/02/26>. printed Aug. 13, 2010.
 Pohl, M. et al., "In vitro testing of artificial heart valves; comparison between Newtonian and non-Newtonian fluids" Artif Argns, Jan. 1996; 20(1); pp. 37-46.
 Purinya, B. et al., "Biomechanical and Structural Properties of the Implanted Bioprosthetic Valve Leaflets" J. of Biomechanis, vol. 27, Iss 1, Jan. 1994 pp. 1-11 Elsevier Science Ltd, 1993.
 Sacks, MS et al., "Bioprosthetic heart valve heterograft biomaterials: structure, mechanical behavior and computational simulation" Expert Rev Med Devices, Nov. 2006; 3(6): pp. 817-834 (Abstract only).
 Sacks, MS et al., "Collagen fiber architecture of bovine pericardium" ASAIO J, Jul. 1, 1994, 40(3), pp. 632-637.
 Sacks, M S et al., "A small angle light scattering device for planar connective tissue microstructural analysis" Ann Biomed Eng, Jul. 1, 1997, 25(4), pp. 678-689.
 Sacks, Michael S, "Incorporation of experimentally-derived fiber orientation into a structural constitutive model for planar collagenous tissues" J. Biomech Eng, Apr. 1, 2003, 125(2), pp. 280-287.
 Sacks, Michael S. et al., "Quantification of the fiber architecture and biaxial mechanical behavior of porcine intestinal submucosa" J of Biomedical Research, vol. 46, Iss 1, Jul. 1999, pp. 1-10.
 Samouillan, V. et al., "Comparison of chemical treatments on the chain dynamics and thermal stability of bovine pericardium collagen" J Biomed Mater Res A. Feb. 1, 2003;64(2), pp. 330-338.
 Schmidt, Dorth et al., "Tissue engineering of heart valves using decellularized xenogeneic of polymeric starter matrices" Philos Trans R Soc Lond B Bio Sci., Aug. 29, 2007, 362(1484); 1505-1512; published online Jun. 22, 2007, doi: 10.1098/rstb.2007.2131.
 Schoen, Frederick J., "Tissue heart valves: Current challenges and future research perspectives" J of Biomedical Materials Research, vol. 47, Iss 4, Dec. 15, 1999, pp. 439-465.
 Sellaro, Tiffany L., "Effects of Collagen Orientation on the Medium-Term Fatigue Response of Heart Valve Biomaterials" 2003, (published thesis) pp. 40-45.
 Sellaro, Tiffany L. et al., "Effects of Collagen Fiber Orientation on the Response of Biologically Derived Soft Tissue Biomaterials to Cyclic Loading" J. Biomed Mater Res A, Jan. 1, 2007; 80(1): 194-205; published online Oct. 13, 2006 by Wiley InterScience.
 Shandas, Robin PhD et al., "A Method for Determining the Reference Effective Flow Areas for Mechanical Heart Valve Prostheses" Circulation Apr. 25, 2000.
 Shen, Ming et al., "Effect of ethanol and ether in the prevention of calcification of bioprostheses" Ann Thorac Surg. May 2001;71(5 Suppl), pp. 413-416.

(56)

References Cited**OTHER PUBLICATIONS**

- Shen, Ming et al., "Protein adsorption in glutaraldehyde-preserved bovine pericardium and porcine valve tissues" *The Annals of Thoracic Surgery*, 2001; 71, pp. 409.
- Simionescu, D et al., "Mapping of glutaraldehyde-treated bovine pericardium and tissue selection for bioprosthetic heart valve" *J. Biomed Mater Res*, Jun. 1, 1993;27(6), pp. 697-704.
- Sun, Wei et al., "Response of heterograft heart valve biomaterials to moderate cyclic loading" *J Biomed Mater Res A*, Jun. 2004, 69(4), pp. 658-669.
- Topol, Eric J., "Textbook of Interventional Cardiology", 1990, Chs. 43-44, pp. 831-867.
- Vyavahare, Narendra et al., "Mechanisms of bioprosthetic heart valve failure: Fatigue causes collagen denaturation and glycosaminoglycan loss" *J of Biomedical Research*, vol. 446, Iss 1, Jul. 1999, pp. 44-50.
- Vyavahare, NR et al., "Prevention of Glutaraldehyde-Fixed Bioprosthetic Heart Valve Calcification by Alcohol Pretreatment: Further Mechanistic Studies" *J Heart Valve Dis*, Jul. 2000;9(4), pp. 561-566.
- Werner, S. et al., "Testing the Hydrodynamic properties of heart valve prostheses with a new test apparatus", *Biomed Tech (Berl)* Sep. 1994; 30(9), pp. 204-210 (Abstract only).
- Wiegner, A W et al., "Mechanical and structural correlates of canine pericardium" *Circ Res*, Sep. 1, 1981; 49(3), pp. 807-814.
- Yasui, Takeshi et al., "Determination of collagen fiber orientation in human tissue by use of polarization measurement of molecular second-harmonic-generation light", *Applied Optics*, vol. 42, No. 14, May 10, 2004, pp. 2861-2867.
- Zioupou, P. et al., "Anisotropic Elasticity and Strength of Glutaraldehyde Fixed Bovine Pericardium for Use in Pericardial Bioprosthetic Valves" *J. Biomed Mater Res*, Jan. 1994, 28(1), pp. 49-57.
- Zioupou, P. et al., "Mechanical and Optical anisotropy of bovine pericardium" *Med Biol Eng Comput*, Jan. 1992; 30 (1); pp. 76-82.
- Office Action issued in U.S. Appl. No. 14/136,516, dated Mar. 10, 2014.
- Notice of Allowance issued in U.S. Appl. No. 14/136,516, dated Mar. 31, 2014.
- Office Action issued in U.S. Appl. No. 10/887,688, dated Nov. 28, 2007.
- Final Office Action issued in U.S. Appl. No. 10/887,688, dated Jul. 15, 2008.
- Office Action issued in U.S. Appl. No. 10/887,688, dated Mar. 16, 2009.
- Examiner Interview Summary issued in U.S. Appl. No. 10/887,688, dated Jun. 12, 2009.
- Final Office Action issued in U.S. Appl. No. 10/887,688, dated Mar. 2, 2010.
- Supplemental Declaration Under 37 CFR 1.131 by inventors filed in U.S. Appl. No. 10/887,688, filed Sep. 14, 2009.
- Supplemental Declaration Under 37 CFR 1.131 by inventors filed in U.S. Appl. No. 10/887,688, filed Feb. 28, 2008.
- Supplemental Declaration Under 37 CFR 1.131 by inventors filed in U.S. Appl. No. 10/887,688, filed Dec. 15, 2008.
- Examiner Interview Summary issued in U.S. Appl. No. 10/887,688, dated Jul. 26, 2010.
- Office Action issued in U.S. Appl. No. 10/887,688, dated Feb. 16, 2012.
- Office Action issued Sep. 29, 2010, issued in U.S. Appl. No. 12/228,192.
- Examiner Interview Summary, dated Apr. 5, 2011 in U.S. Appl. No. 12/228,192.
- Final Office Action issued Jul. 14, 2011, in U.S. Appl. No. 12/228,192.
- Office Action issued in U.S. Appl. No. 10/037,266, dated May 8, 2003.
- Final Office Action issued in U.S. Appl. No. 10/037,266, dated Mar. 9, 2004.
- Hilbert et al., "Biomechanics: Allograft Heart Valves," *Cardiac Reconstructions with Allograft Tissues*, Springer, New York (2005), pp. 210-212.
- Office Action issued Jul. 8, 2014, in U.S. Appl. No. 14/253,656.
- Office Action issued Aug. 15, 2014, in U.S. Appl. No. 14/284,063.
- Notice of Allowance issued Oct. 7, 2014, in U.S. Appl. No. 14/253,656.
- Office Action issued Sep. 11, 2014, in U.S. Appl. No. 14/268,190.
- Office Action issued Sep. 3, 2014, in U.S. Appl. No. 14/284,049.
- Office Action issued Sep. 12, 2014, in U.S. Appl. No. 14/268,184.
- Final Office Action issued Sep. 25, 2014, in U.S. Appl. No. 14/253,656.
- Final Office Action issued May 8, 2015 in U.S. Appl. No. 14/502,453.
- Office Action issued Dec. 5, 2014 in U.S. Appl. No. 14/502,453.
- Declaration Under 37 CFR 1.131 as filed in U.S. Appl. No. 10/887,688 on Dec. 15, 2008, by co-inventors of that application.
- Cross-reference is made to U.S. Appl. No. 14/502,453, filed Sep. 30, 2014, and its associated Preliminary Amendment.
- Affidavit of Dr. Paolo Angelini, M.D., signed Aug. 25, 2009.
- Affidavit of Dr. Gervasio A. Lamas, M.D., signed Sep. 3, 2009.
- Andersen, H.R. et al., "Transluminal implantation of artificial heart valve" *European Heart Journal*, 1992, 13, pp. 704-708.
- "Artificial heart valve" http://en.wikipedia.org/Artificial_heart_valve, printed May 13, 2009.
- Bonhoeffer, Philipp M.D. et al., "Percutaneous Insertion of the Pulmonary Valve" *J of the Amer College of Cardiology*, vol. 39, No. 10, Elsevier Science, Inc. 2002, pp. 1664-1669, London, UK, and Paris, FR.
- Bonhoeffer, Philipp et al., "Percutaneous replacement of pulmonary valve in a right-centricle to pulmonary-artery prosthetic conduit with valve dysfunction" *Early Report, The Lancet*, vol. 356, Oct. 21, 2000, pp. 1403-1405.
- Bonhoeffer, Philipp et al., "Transcatheter Implantation of a Bovine Valve in Pulmonary Position: A Lamb Study" *Circulation J. of the Amer Heart Assoc*, 2000; 102; pp. 813-816.
- Boudjemline, Younes et al., "Percutaneous pulmonary valve replacement in a large right ventricular outflow tract: An experimental study" *J. Am. Coll. Cardiol.* 2004; 43; pp. 1082-1087.
- Braga-Vilela, A. et al., "Extracellular Matrix of Porcine Pericardium; Biochemistry and Collagen Architecture" *J. Membr Biol.*, 2008.
- Breuer, Christopher K. M.D. et al., "Application of Tissue-Engineering Principles toward the Development of a Semilunar Heart Valve Substitute" *Tissue Engineering*, vol. 10, No. 11/12, 2004, pp. 1725-1736.
- Cale, A.R. et al., "Revisited: a descending thoracic aortic valve to treat prosthetic valve insufficiency" *Ann Thorac Surg*, May 1993, 55(5), pp. 1218-1222.
- Cerrolaza, M et al., "A comparison of the hydrodynamical behaviour of three heart aortic prostheses by numerical methods".
- Chew, G.G. et al., Abstract for "Simulation of Damage in a Porcine Prosthetic Heart Valve" *J. Med. Eng. Technol.*, Sep.-Oct. 1999; 23(5): 178-89 (Abstract only).
- Christie G.W. et al., Abstract for "On Stress Reduction in Bioprosthetic Heart Valve Leaflets by the Use of a Flexible Stent" *J. Card Surg*, Dec. 1991; 6(4) pp. 476-481 (Abstract only).
- "Collagen" <http://en.wikipedia.org/wiki/Collagen>, printed May 13, 2009.
- Collins, J. J., Jr., "The Evolution of artificial heart valve" *N. Engl J Med*, Feb. 28, 1991; vol. 324(9), pp. 624-626.
- Corden, J. et al., "The influence of open leaflet geometry on the haemodynamic flow characteristics of polyurethane trileaflet artificial heart valve" *PubMed medline query*, p. 1 of 1.
- Cribier, Alain et al., "Percutaneous Transcatheter Implantation of an Aortic Valve Prosthesis for Calcific Aortic Stenosis: First Human Case Description" *Circulation J of the Amer Heart Assoc*, originally published online Nov. 25, 2002.
- Edwards Lifesciences Receives FDA Approval for New Heart Valve, <http://www.medicalnewstoday.com/articles/149588.php>, May 11, 2009.
- Fish, R. David, "Percutaneous Heart Valve Replacement: Enthusiasm Tempered" *Circulation J of the Amer Heart Assoc*, 2004; vol. 110; pp. 1876-1878.

(56)

References Cited**OTHER PUBLICATIONS**

Fishbein, M.C. et al., "Cardiac pathology after aortic valve replacement using Hufnagel trileaflet prostheses: study of 20 necropsy patients" *Ann Heart J.*, Apr. 1975, 89(4), pp. 443-448.

Gloeckner, D. Claire et al., "Mechanical Evaluation and Design of a Multilayered Collagenous Repair Biomaterial" *J. of Biomedical Materials Research Part A*, vol. 52 Iss 2, pp. 365-373, Published online Aug. 15, 2000, Wiley Periodicals, Inc.

Grube, et al., "Progress and Current Status of Percutaneous Aortic Valve Replacement: Results of Three Device Generations of the CoreValve Revalving System", *Circ. Cardiovasc Intervent.* 2008;1:167-175 (Abstract only).

Hanlon, JG et al., "Pre-use intraoperative testing of autologous tissue for valvular surgery: a proof of concept study" *J. Heart Valve Dis.* Nov. 1999; 8(6); pp. 614-623.

Bech-Hanssen, Odd, M.D. et al., "Aortic Prosthetic Valve Design and Size: Relation to Doppler Echocardiographic Finding and Pressure Recovery—An In Vitro Study" *J. Am Soc Echocardiography* 2000; vol. 13, pp. 39-50.

Hasenkam, J.M. et al., "A model for acute haemodynamic studies in the ascending aorta in pigs" *Cardiovasc Res.* Jul. 1988, 22(7), pp. 464-471.

Hiester, E.D. et al., "Optimal bovine pericardial tissue selection sites. I. Fiber architecture and tissue thickness measurements." *J. Biomed Mater Res.* Feb. 1, 1998; 39(2), pp. 207-214.

Hufnagel, Charles A., M.D., "Basic Concepts in the Development of Cardiovascular Prostheses" *The American Journal of Surgery*, vol. 137, Mar. 1979.

Hufnagel, Charles A., MD et al., "In the beginning. Surgical Correction of Aortic Insufficiency" 1954; *Ann Thorac Surg* May 1989; 47(3), pp. 475-476.

Hufnagel, Charles A., MD et al., "Late follow-up of ball-valve prostheses in the descending thoracic aorta", *J. Thorac Cardiovasc Surg.* Dec. 1976, 72(6), pp. 900-909.

Hufnagel, Charles A., MD et al., "Surgical Correction of Aortic Insufficiency" *Surgery* vol. 35, May 1954 No. 5.

Hufnagel, Charles A., "Vessels and Valves", Sec. 1: Development of Cardiac Surgery, Chap 7, pp. 43-55.

Introduction to Stereomicroscopy, <http://www.microscopyu.com/articles/stereomicroscopy/stereointro.html>, Copyright 2000-2012, printed on Mar. 15, 2012.

IOPATCH(R) Tutoplast(R) Processed Pericardium Directions for Use; http://www.iopinc.com/surgeons_and_medical_professionals/iopatch/directions.asp, printed on Jun. 2, 2009.

Knudsen, L.L. et al., "Catheter-implanted prosthetic heart valves. Transluminal catheter implantation of a new expandable artificial heart valve in the descending thoracic aorta in isolated vessels and closed chest pigs" *Int J. Artif Organs*, May 1993, 16(5); pp. 253-262.

Lax, Jorge A., M.D., et al., "Estimation of the Ejection Fraction in Patients with Myocardial Infarction Obtained from the Combined Index of Systolic and Diastolic Left Ventricular Function: A New Method" *J of the American Soc of Echocardiography*, vol. 13, No. 2.

Liao, Jun et al., "Molecular orientation of collagen in intact planar connective tissues under biaxial stretch" *Acta Biomaterialia*, vol. 1, Iss. 1, Jan. 2005, pp. 45-54.

Liao, K X et al., "Two-dimensional mechanical and ultrastructural correlates of bovine pericardium for prosthetic valves" *ASAIO Trans.* Jun. 1, 1991, 37(3); pp. 341-351.

Li, Yu et al., "New Polyurethane valves in new soft artificial heart" *ASAIO Trans* Jul.-Sep. 1989; 35(3), pp. 301-304.

Mendelson, Karen et al., "Heart Valve Tissue Engineering: Concepts, Approaches, Progress, and Challenges" *Ann Biomed Eng.* Dec. 2006; 34(12); 1799-1819; published online Oct. 12, 2006 doi:10.1007/s10439-006-9163-z.

Mirajafi, A. et al., "The effects of collagen fiber orientation of the flexural properties of pericardial heterograft biomaterials" *Biomaterials*, Mar. 2005; 26(7); pp. 795-804.

Mirzaie, M. et al., "A new storage solution for porcine aortic valves" *Ann Thorac Cardiovasc Surg.* Apr. 2007; 13(2), pp. 102-109.

Moazami, N. et al., "Transluminal aortic valve placement. A feasibility study with a newly designed collapsible aortic valve" *ASAIO J.* Sep.-Oct. 1996, 42(5), pp. 381-385.

Nienaber C., M.D. et al., "Nonsurgical Reconstruction of Thoracic Aortic Dissection by Stent-Graft Placement" *N. Eng. J. Med.* May 20, 1999, col. 340, No. 20.

Noorlander, Maril L. et al., "A Quantitative Method to Determine the Orientation of Collagen Fibers in the Dermis" *The J. of Histochemistry & Cytochemistry*, vol. 50(11): 2002, pp. 1469-1474.

Nunn, D.B., "Structural Failure of Dacron Arterial Grafts" *Seminars in Vascular Surgery*, col. 12, No. 1 Mar. 1999, pp. 88-91.

Optical Microscope, Wikipedia, http://en.wikipedia.org/wiki/Optical_Microscope, May 13, 2009.

Orthogonality, <http://en.wikipedia.org/wiki/Orthogonal>, May 13, 2009.

Paniagua, David, et al., Percutaneous Heart Valve in the Chronic In Vitro Testing Model, *Circulation*, 2002, pp. 51-52, vol. 106, American Heart Association, US.

Paniagua, David et al., First Human Case of Retrograde Transcatheter Implantation of an Aortic Valve Prosthesis, *Texas Heart Institute Journal*, 2005, pp. 91-96, vol. 32, US.

* cited by examiner




FIG. 1




FIG.2




FIG.3A




FIG. 3B




FIG.4




FIG. 5




FIG.6




FIG. 7




FIG.8




FIG. 9A




FIG. 9B




FIG. 9C

1

PERCUTANEOUS REPLACEMENT HEART VALVE AND A DELIVERY AND IMPLANTATION SYSTEM

CONTINUITY INFORMATION

The present application is a continuation application of U.S. patent application Ser. No. 13/675,665 filed on Nov. 13, 2012, which is a continuation application of U.S. patent application Ser. No. 10/887,688 filed on Jul. 10, 2004, now U.S. Pat. No. 8,308,797, which is a continuation-in-part application of U.S. patent application Ser. No. 10/037,266, filed on Jan. 4, 2002 (now abandoned). All of the foregoing applications are incorporated herein by reference in their entireties.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention is in the field of heart valve replacement. More specifically, the present invention is directed to a method of making a percutaneously implantable replacement heart valve.

2. Description of Related Art

There have been numerous efforts in the field of heart valve replacement to improve both the durability and effectiveness of replacement heart valves as well as the ease of implantation. A brief description of heart valves and heart function follows to provide relevant background for the present invention.

There are four valves in the heart that serve to direct the flow of blood through the two sides of the heart in a forward direction. On the left (systemic) side of the heart are: 1) the mitral valve, located between the left atrium and the left ventricle, and 2) the aortic valve, located between the left ventricle and the aorta. These two valves direct oxygenated blood coming from the lungs through the left side of the heart into the aorta for distribution to the body. On the right (pulmonary) side of the heart are: 1) the tricuspid valve, located between the right atrium and the right ventricle, and 2) the pulmonary valve, located between the right ventricle and the pulmonary artery. These two valves direct de-oxygenated blood coming from the body through the right side of the heart into the pulmonary artery for distribution to the lungs, where it again becomes re-oxygenated to begin the circuit anew.

Heart valves are passive structures that simply open and close in response to differential pressures on either side of the particular valve. They consist of moveable "leaflets" that are designed simply to open and close in response to differential pressures on either side of the valve's leaflets. The mitral valve has two leaflets and the tricuspid valve has three. The aortic and pulmonary valves are referred to as "semilunar valves" because of the unique appearance of their leaflets, which are more aptly termed "cusps" and are shaped somewhat like a half-moon. The aortic and pulmonary valves each have three cusps.

In general, the components of heart valves include the valve annulus, which will remain as a roughly circular open ring after the leaflets of a diseased or damaged valve have been removed; leaflets or cusps; papillary muscles which are attached at their bases to the interior surface of the left or right ventricular wall; and multiple chordae tendineae, which couple the valve leaflets or cusps to the papillary muscles. There is no one-to-one chordal connection between the leaflets and the papillary muscles; instead, numerous chordae are present, and chordae from each papillary muscle attach to both of the valve leaflets.

2

When the left ventricular wall relaxes so that the ventricular chamber enlarges and draws in blood, the leaflets of the mitral valve separate and the valve opens. Oxygenated blood flows in a downward direction through the valve, to fill the expanding ventricular cavity. Once the left ventricular cavity has filled, the left ventricle contracts, causing a rapid rise in the left ventricular cavity pressure. This causes the mitral valve to close while the aortic valve opens, allowing the oxygenated blood to be ejected from the left ventricle into the aorta. The chordae tendineae of the mitral valve prevent the mitral leaflets from prolapsing back into the left atrium when the left ventricular chamber contracts.

The three leaflets, chordae tendineae, and papillary muscles of the tricuspid valve function in a similar manner, in response to the filling of the right ventricle and its subsequent contraction. The cusps of the aortic valve also respond passively to pressure differentials between the left ventricle and the aorta. When the left ventricle contracts, the aortic valve cusps open to allow the flow of oxygenated blood from the left ventricle into the aorta. When the left ventricle relaxes, the aortic valve cusps reapproximate to prevent the blood which has entered the aorta from leaking (regurgitating) back into the left ventricle. The pulmonary valve cusps respond passively in the same manner in response to relaxation and contraction of the right ventricle in moving de-oxygenated blood into the pulmonary artery and thence to the lungs for re-oxygenation. Neither of these semilunar valves has associated chordae tendineae or papillary muscles.

Problems that can develop with heart valves consist of stenosis, in which a valve does not open properly, and/or insufficiency, also called regurgitation, in which a valve does not close properly. In addition to stenosis and insufficiency of heart valves, heart valves may need to be surgically repaired or replaced due to certain types of bacterial or fungal infections in which the valve may continue to function normally, but nevertheless harbors an overgrowth of bacteria (vegetation) on the leaflets of the valve that may embolize and lodge downstream in a vital artery. If such vegetations are on the valves of the left side (i.e., the systemic circulation side) of the heart, embolization may occur, resulting in sudden loss of the blood supply to the affected body organ and immediate malfunction of that organ. The organ most commonly affected by such embolization is the brain, in which case the patient suffers a stroke. Thus, surgical replacement of either the mitral or aortic valve (left-sided heart valves) may be necessary for this problem even though neither stenosis nor insufficiency of either valve is present. Likewise, bacterial or fungal vegetations on the tricuspid valve may embolize to the lungs resulting in a lung abscess and therefore, may require replacement of the tricuspid valve even though no tricuspid valve stenosis or insufficiency is present.

These problems are treated by surgical repair of valves, although often the valves are too diseased to repair and must be replaced. If a heart valve must be replaced, there are currently several options available, and the choice of a particular type of artificial valve depends on factors such as the location of the valve, the age and other specifics of the patient, and the surgeon's experiences and preferences. Currently in the United States over 100,000 defective heart valves are replaced annually, at an approximate cost of \$30-50,000 per procedure, and thus it would be desirable if heart valves could be replaced using minimally invasive techniques and without having to repeat the procedure within a matter of years due to the lack of durability of the replacement heart valve. It would be especially advantageous if a defective heart valve could be removed via an endovascular procedure, that is, a procedure where the invasion into the body is through a blood vessel

3

such as the femoral artery. The procedure is then carried out percutaneously and transluminally using the vascular system to convey appropriate devices to the position in the body wherein it is desired to carry out the desired procedure. An example of such a procedure would be angioplasty, wherein a catheter carrying a small balloon at its distal end is manipulated through the body's vessels to a point where there is a blockage in a vessel. The balloon is expanded to create an opening in the blockage, and then the balloon is deflated and the catheter and balloon are removed from the vessel.

Endovascular procedures have substantial benefits both from the standpoint of health and safety as well as cost. Such procedures require minimal invasion of the human body, and there is consequently considerable reduction and in some instances even elimination, of the use of a general anesthesia and much shorter hospital stays.

Replacement heart valves can be categorized as either artificial mechanical valves, transplanted valves and tissue valves. Replacement heart valves are designed to optimize hemodynamic performance, thrombogenicity and durability. Another factor taken into consideration is the relative ease of surgical implantation.

Mechanical valves are typically constructed from nonbiological materials such as plastics, metals and other artificial materials which, while durable, are expensive and prone to blood clotting which increases the risk of an embolism. Anticoagulants taken to help against blood clotting can further complicate the patient's health due to increased risks for hemorrhages.

Transplanted valves are natural valves taken from cadavers. These valves are typically removed and frozen in liquid nitrogen, and are stored for later use. They are typically fixed in glutaraldehyde to eliminate antigenicity and are sutured in place, typically with a stent.

Artificial tissue valves are valves constructed from animal tissue, such as bovine or porcine tissue. Efforts have also been made at using tissue from the patient for which the valve will be constructed.

Most tissue valves are constructed by sewing the leaflets of pig aortic valves to a stent to hold the leaflets in proper position, or by constructing valve leaflets from the pericardial sac of cows or pigs and sewing them to a stent. The porcine or bovine tissue is chemically treated to alleviate any antigenicity. The pericardium is a membrane that surrounds the heart and isolates it from the rest of the chest wall structures. The pericardium is a thin and very slippery, which makes it difficult for suturing in a millimetrically precise way. The method of making the replacement heart valve of the present invention solves this problem through a process that includes drying and compressing the pericardium using photo-mechanical compression in such a way that makes it possible to handle and fold the material more easily.

For example, one prior replacement heart valve requires each sculpted leaflet to be trimmed in a way that forms an extended flap, which becomes a relatively narrow strand of tissue near its tip. The tip of each pericardial tissue strand is sutured directly to a papillary muscle, causing the strand to mimic a chordae tendineae. Each strand extends from the center of a leaflet in the valve, and each strand is sutured directly to either an anterior and posterior papillary muscle. This requires each leaflet to be positioned directly over a papillary muscle. This effectively rotates the leaflets of the valve about 90 degrees as compared to the leaflets of a native valve. The line of commissure between the leaflets, when they are pressed together during systole, will bisect (at a perpen-

4

dicular angle) an imaginary line that crosses the peaks of the two papillary muscles, instead of lying roughly along that line as occurs in a native valve.

A different approach to creating artificial tissue valves is described in U.S. Pat. No. 5,163,955 to Calvin, et al. and U.S. Pat. Nos. 5,571,174 and 5,653,749 to Love. Using a cutting die, the pericardial tissue is cut into a carefully defined geometric shape, treated with glutaraldehyde, then clamped in a sandwich-fashion between two stent components. This creates a tri-leaflet valve that resembles an aortic or pulmonary valve, having semilunar-type cusps rather than atrioventricular-type leaflets.

U.S. Pat. No. 3,671,979 to Mouloupoulos describes an endovascularly inserted conical shaped umbrella-like valve positioned and held in place by an elongated mounting catheter at a supra-annular site to the aortic valve in a nearby arterial vessel. The conical end points toward the malfunctioning aortic valve and the umbrella's distal ends open up against the aorta wall with reverse blood flow, thereby preventing regurgitation.

U.S. Pat. No. 4,056,854 to Boretos describes an endovascularly inserted, catheter mounted, supra-annular valve in which the circular frame abuts the wall of the artery and attached flaps of flexible membrane extend distally in the vasculature. The flaps lie against the artery wall during forward flow, and close inward towards the central catheter to prevent regurgitation during reverse blood flow. The Boretos valve was designed to be positioned against the artery wall during forward flow, as compared to the mid-center position of the Mouloupoulos valve, to reduce the stagnation of blood flow and consequent thrombus and embolic formation expected from a valve at mid-center position.

The main advantage of tissue valves is that they do not cause blood clots to form as readily as do the mechanical valves, and therefore, they do not absolutely require systemic anticoagulation. The major disadvantage of tissue valves is that they lack the long-term durability of mechanical valves. Tissue valves have a significant failure rate, usually within ten years following implantation. One cause of these failures is believed to be the chemical treatment of the animal tissue that prevents it from being antigenic to the patient. In addition, the presence of extensive suturing prevents the artificial tissue valve from being anatomically accurate in comparison to a normal heart valve, even in the aortic valve position.

A shortcoming of prior artificial tissue valves has been the inability to effectively simulate the exact anatomy of a native heart valve. Although transplanted human or porcine aortic valves have the gross appearance of native aortic valves, the fixation process (freezing with liquid nitrogen, and chemical treatment, respectively) alters the histologic characteristics of the valve tissue. Porcine and bovine pericardial valves not only require chemical preparation (usually involving fixation with glutaraldehyde), but the leaflets must be sutured to cloth-covered stents in order to hold the leaflets in position for proper opening and closing of the valve. Additionally, the leaflets of most such tissue valves are constructed by cutting or suturing the tissue material, resulting in leaflets that do not duplicate the form and function of a real valve and are more susceptible to failure.

SUMMARY OF THE INVENTION

The present invention is a replacement heart valve device and method of making same. The replacement heart valve device, in a preferred embodiment, comprises a stent made of stainless steel or self-expanding nitinol and a completely newly designed artificial biological tissue valve disposed

5

within the inner space of the stent. The cusp or leaflet portion of the valve means is formed by folding of the pericardium material preferably used to create the valve without cutting of slits to form leaflets or suturing or otherwise affixing of separate leaflet portions. Other forms of tissue and suitable synthetic materials can also be used for the valve, formed in a sheet of starting material. The folded design provides a number of advantages over prior designs, including improved resistance to tearing at suture lines. The cusps/leaflets open in response to blood flow in one direction and close in response to blood flow in the opposite direction. Preferably the tubular portion of the valve means contains the same number of cusps as the native valve being replaced, in substantially the same size and configuration. The outer surface of the valve means is attached to the stent member.

The replacement heart valve device is preferably implanted using a delivery system having a central part which consists of a flexible hollow tube catheter that allows a metallic guide wire to be advanced inside it. The stented valve is collapsed over the central tube and it is covered by a movable sheath. The sheath keeps the stented valve in the collapsed position. Once the cover sheath is moved backwards, the stented valve can be deployed. The endovascular stented-valve, in a preferred embodiment, is a glutaraldehyde fixed mammal pericardium or synthetic biocompatible material which has two or three cusps that open distally to permit unidirectional blood flow. The stent can either be self-expanding or the stent can be expandable through use of a balloon catheter.

The present invention also comprises a method of making a replacement heart valve device. In order to make the valve, the pericardium starting material is isolated and all the fat tissue and extra fibers are removed. The biological membrane material is cleaned by mechanical separation of unwanted layers using hydromechanical force means. Once the pericardium is completely clean, the material is dried in order to make it easier to handle and fold. Preferably, this drying is done by exposing the biocompatible membrane material to photomechanical compression to remove all lipids from the pericardium or other biocompatible membrane material and to cause protein denaturalization, transforming the material into a stronger and more homogeneous surface. The valve is formed by taking a flat sheet of the material and folding in such a way that forms a three-leaflet or other number of leaflet valve. Then it is placed in a sequence of solutions, one of isopropyl alcohol of about 70-100%, one of ethanol of about 70-100%, one of glycerol and one of glutaraldehyde, preferably at a concentration of about 0.07-25% for approximately 36 hours. The material is dried in order to make it easier to handle and fold. Preferably this drying is done by exposing the biocompatible membrane material to light and then mechanically compressing the material to cause protein denaturation. This results in material that is stronger and more homogeneous. The valve is formed by taking a flat sheet of bovine or porcine pericardium and folding it in such a way that forms a three-leaflet valve. The valve can also be made in the same manner from fresh, cryopreserved or glutaraldehyde fixed allografts or xenografts or synthetic non-biological, non-thrombogenic material. The folding of the pericardium material to create the cusps or leaflets reduces the extent of suturing otherwise required, and resembles the natural form and function of the valve leaflets. The cleaning, pressing and drying technique used to create the valve material makes the folding more practicable. The valve is rehydrated after being formed. The method of the present invention also greatly reduces the risk of tearing of the cusps or leaflets, since they are formed by folding a single uncut portion of material forming the valve rather than being attached by suturing.

6

Once the endovascular implantation of the prosthetic valve device is completed in the host, the function of the prosthetic valve device can be monitored by the same methods as used to monitor valve replacements done by open heart surgery. Routine physical examination, periodic echocardiography or angiography can be performed. In contrast to open heart surgery, however, the host requires a short recovery period and can return home within one day of the endovascular procedure. The replacement heart valve device of the present invention can be used in any patient where bioprosthetic valves are indicated, namely elderly patients with cardiac valve diseases, and patients unable to tolerate open heart procedures or life-long anticoagulation medication and treatment. The present invention can be practiced in applications with respect to each of the heart's valves.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 depicts a side perspective view of the replacement heart valve device of the present invention in one embodiment with the valve in the closed position.

FIG. 2 depicts the folds which form the leaflets or cusps of the replacement heart valve of the present invention in one embodiment.

FIGS. 3A and 3B depict a preferred procedure for folding the pericardium tissue starting material to create the replacement heart valve of the present invention.

FIG. 4 depicts a side perspective view of the replacement heart valve device of the present invention in one embodiment represented as if implanted within an artery.

FIG. 5 depicts a side view of one embodiment of the replacement heart valve device of the present invention mounted within a self-expanding stent, with the stent in the expanded position.

FIG. 6 depicts a side perspective view of one embodiment of the replacement heart valve device of the present invention mounted within a self-expanding stent in the collapsed position.

FIG. 7 depicts the suture points of one embodiment of the replacement heart valve device of the present invention.

FIG. 8 depicts the implantation/delivery system used with the present invention in a preferred embodiment.

FIGS. 9A, 9B and 9C depict a representation of a sheet of biocompatible valve material showing preferred folds.

DESCRIPTION OF A PREFERRED EMBODIMENT

The present invention comprises a percutaneously implantable replacement heart valve and a method for making same. The artificial heart valve device of the present invention is capable of exhibiting a variable diameter between a compressed or collapsed position and an expanded position. A preferred embodiment of the replacement heart valve device according to the present invention is set forth in FIG. 5. The replacement heart valve device comprises a stent member **100** and a flexible valve means **200**. The stent member **100** is preferably self-expanding, although balloon-expandable stents can be used as well, and has a first polygonal shape in its compressed or collapsed configuration and a second, larger polygonal shape in its expanded configuration. Referring to FIG. 1, the valve means **200** comprises a generally tubular portion **210** and, preferably, a peripheral upstanding cusp or leaflet portion **220**. The valve means **200** is disposed within the cylindrical stent member **100** with the tubular portion **210** transverse of and at some acute angle relative to the stent walls. The diameter of the tubular portion **210** is

7

substantially the same as the inside diameter of the stent member in its initial expanded configuration. The peripheral upstanding cusp or leaflet portion **220** is disposed on valve means **200** substantially parallel to the walls of the stent member similar to a cuff on a shirt. The cusp or leaflet portion **220** of the valve means **200** is generally tubular in shape and comprises three leaflets **221**, **222** and **223** as shown, although it is understood that there could be from two to four leaflets. The tubular portion of the valve means **200** is attached to the stent member **100** by a plurality of sutures **300**, as depicted in FIG. 7.

The leaflet portion **220** of the valve means **200** extends across or transverse of the cylindrical stent **100**. The leaflets **221**, **222** and **223** are the actual valve and allow for one-way flow of blood. The leaflet portion **220** as connected to the rest of the valve resembles the cuff of a shirt. FIG. 9 depicts the folds preferred for valve cusp and leaflet formation involving three leaflets. The configuration of the stent member **100** and the flexible, resilient material of construction allows the valve to collapse into a relatively small cylinder as seen in FIG. 6. The replacement heart valve will not stay in its collapsed configuration without being restrained. Once the restraint is removed, the self-expanding stent member **100** will cause the artificial heart valve to take its expanded configuration, as seen in FIG. 5.

Stent Member

The stent member **100** preferably comprises a self-expanding nickel-titanium alloy stent, also called "nitinol," in a sine wave-like configuration as shown in FIG. 5. An enlarged view of a preferred embodiment of the stent member for use in the replacement heart valve of the invention is depicted in FIG. 5. The stent member **100** includes a length of wire **110** formed in a closed zigzag configuration. The wire can be a single piece, stamped or extruded, or it could be formed by welding the free ends together. The straight sections of the stent member **100** are joined by bends. The stent is readily compressible to a small cylindrical shape as depicted in FIGS. 6 and 8, and resiliently self-expandable to the shape shown in FIG. 5.

The stent member **100** of the artificial heart valve device of the present invention may be made from various metal alloys, titanium, titanium alloy, nitinol, stainless steel, or other resilient, flexible non-toxic, non-thrombogenic, physiologically acceptable and biocompatible materials. The configuration may be the zigzag configuration shown or a sine wave configuration, mesh configuration or a similar configuration which will allow the stent to be readily collapsible and self-expandable. When a zigzag or sine wave configured stent member is used, the diameter of the wire from which the stent is made is preferably from about 0.010 to 0.035 inches and still, preferably from about 0.012 to 0.025 inches. The diameter of the stent member will be from about 1.5 to 3.5 cm, preferably from about 1.75 to 3.00 cm, and the length of the stent member will be from about 1.0 to 10 cm, preferably from about 1.1 to 5 cm.

The stent used in a preferred embodiment of the present invention is fabricated from a "shaped memory" alloy, nitinol, which is composed of nickel and titanium. Nitinol wire is first fashioned into the desired shape for the device and then the device is heat annealed. A meshwork of nitinol wire of approximately 0.008 inch gauge is formed into a tubular structure with a minimum central diameter of 20 mm to make the stent. Away from its central portion, the tubular structure flares markedly at both ends in a trumpet-like configuration. The maximum diameter of the flared ends of the stent is approximately 50 mm. The purpose of the stent is to maintain a semi-rigid patent channel through the diseased cardiac valve following its implantation.

8

When the components of the replacement heart valve device are exposed to cold temperatures, they become very flexible and supple, allowing them to be compressed down and pass easily through the delivery sheath. A cold temperature is maintained within the sheath during delivery to the deployment site by constantly infusing the sheath with an iced saline solution. Once the valve components are exposed to body temperature at the end of the sheath, they instantaneously reassume their predetermined shapes, thus allowing them to function as designed.

Preferably the stent member **100** carries a plurality of barbs extending outwardly from the outside surface of the stent member for fixing the heart valve device in a desired position. More preferably the barbs are disposed in two spaced-apart, circular configurations with the barbs in one circle extending in an upstream direction and the barbs in the other circle extending in a downstream direction. It is especially preferable that the barbs on the inflow side of the valve point in the direction of flow and the barbs on the outflow side point in the direction opposite to flow. It is preferred that the stent be formed of titanium alloy wire or other flexible, relatively rigid, physiologically acceptable material arranged in a closed zigzag configuration so that the stent member will readily collapse and expand as pressure is applied and released, respectively.

Valve Means

The valve means **200** is flexible, compressible, host-compatible, and non-thrombogenic. The valve means **200** can be made from various materials, for example, fresh, cryopreserved or glutaraldehyde fixed allografts or xenografts. Synthetic biocompatible materials such as polytetrafluoroethylene, polyester, polyurethane, nitinol or other alloy/metal foil sheet material and the like may be used. The preferred material for the valve means **200** is mammal pericardium tissue, particularly juvenile-age animal pericardium tissue. The valve means **200** is disposed within the cylindrical stent member **100** with the tubular portion **210** transverse of and at some acute angle relative to the stent walls. The diameter of the tubular portion **210** is substantially the same as the inside diameter of the stent member **100** in its initial expanded configuration. The peripheral upstanding cusp or leaflet portion **220** is disposed substantially parallel to the walls of the stent member **100** similar to a cuff on a shirt.

The cusp or leaflet portion **220** of the valve means **200** is formed by folding of the pericardium material used to create the valve. FIGS. 3A and 3B depict the way the sheet of heart valve starting material is folded. The starting material is preferably a flat dry sheet, which can be rectangular or other shaped. The cusps/leaflets **221**, **222** and **223** open in response to blood flow in one direction and close in response to blood flow in the opposite direction. Preferably the cusp or leaflet portion **220** of the valve means **200** contains the same number of cusps as the native valve being replaced, in substantially the same size and configuration. FIGS. 9A-9C depict a preferred configuration for folds to create the leaflets/cusps. The leaflet forming portion is a single, continuous, uncut layer affixed to the interior of the cuff layer to form the leaflets/cusps, unlike prior efforts that have involved suturing of three separate leaflet/cusp portions onto the main valve body portion. The leaflets are formed from the free edge of the material after forming the cuff portion. Referring now to FIGS. 9A, 9B, and 9C, with flat sheet on a table, a person facing the sheet would create a cuff at the upper border of sheet by folding the horizontal top edge away/downwardly (fold no. 1). The leaflet portion is formed by folding the sheet's lower half towards the folder/upwardly, as shown in FIG. 9A (fold no. 2). The sheet, now with the upper cuff and bottom inward fold, is folded

inwardly at two preferably equidistant vertical points as shown in FIG. 9B to create the leaflet/cusp portion (folds nos. 3 and 4). The leaflets/cusps are formed by folding fold nos. 6, 7 and 8 after the two opposite vertical edges of sheet are joined to create a cylindrical valve shape, depicted in FIGS. 1 and 3B. The inner leaflet layer is preferably attached to the outer cuff layer by curved or straight continuous suturing. Although a preferred embodiment of the invention comprises a single piece of valve material folded to create the valve body and a leaflet-forming portion that has no cuts or sutures, the inventors have discovered that as long as the leaflet portion of the valve itself is formed from a single piece of biocompatible valve material, the other portions of the valve can be formed by suturing of one or more separate pieces of material without losing the novel and improved qualities of the present invention. This allows for the valve to be made even stronger, more durable and easier to make. This alternate embodiment comprises a leaflet forming layer made of a single piece of valve material attached to a separate piece forming the valve body having a folded cuff portion. The single piece leaflet forming layer is preferably cylindrical in shape and can be formed with or without folding. In this embodiment the single piece leaflet layer can itself be attached to the stent with or without a cylindrical cuff portion. Attachment is preferably by suturing, particularly continuous single or double sutures.

Method of Making Replacement Heart Valve Device

The present invention also comprises a method of making a replacement heart valve device. In order to make the valve, the biocompatible tissue material is isolated and all the fat tissue and extra fibers are removed. Cleaning is preferably accomplished by using a hydromechanical force-based cleaning device to separate tissue layers and hydration with distilled water to remove unwanted layers. Once the pericardium is completely clean, it is subjected to photo-mechanical compression, then the valve is formed and placed in sequential solutions of isopropyl alcohol of about 70-100%, ethanol of about 70-100%, glycerol and glutaraldehyde preferably at a concentration of about 0.07-25% for about 36 hours, respectively. The material is preferably photomechanically compressed to remove lipids and produce protein coagulation to make the surface smoother and more compact and biocompatible, decreasing the molecular distance of collagen fibers. The exposure to light and mechanical compression cause protein denaturation making the material stronger and more homogeneous and biocompatible. Gas sterilization can also be used to sterilize the tissue membrane material. The valve is formed by taking a flat sheet of the material and folding it in such a way that forms a three-leaflet or desired number of leaflet valve as shown in FIGS. 3A and 3B and/or FIGS. 9A, 9B and 9C. The folding of the pericardium material to create the cusps or leaflets reduces the extent of suturing otherwise required, and resembles the natural form and function of the valve leaflets. It also greatly reduces the risk of tearing of the cusps or leaflets, since they are integral to the valve rather than being attached by suturing.

In a preferred embodiment, the single continuous piece of membrane is folded inward to form an inner leaflet layer within the outer cuff. The single leaflet layer is then attached to the cuff layer to form valve cusps in one of three preferred ways: (i) by curved or straight continuous single or double sutures that affix and form the bases or recesses of the valve cusps; (ii) by lengthwise suture lines attaching the leaflet layer to the cuff layer with the bases or recesses of the valve cusps being thus formed of the folded edge of the membrane; (iii) by further folding of the membrane into lengthwise pleats secured by lengthwise suture attaching the leaflet layer to the cuff layer with the bases or recesses of the valve cusps being

thus formed of the folded edge of the membrane, done for the purpose of giving greater strength and durability to the attachment points of the leaflet layer.

In order to make the pericardium material less slippery and easier to fold, the pericardium is dried, preferably with artificial light using a multi-watt lamp with the pericardium or other biocompatible membrane material placed in a flat aluminum surface to dry it homogeneously. A photomechanical drying machine can also be used. The final result is a homogeneous tissue that looks like plastic paper and makes it easy to manipulate to fold and suture the valve. Once the valve is formed, it is re-hydrated by placing it in a solution of water and 70% alcohol. In approximately 3 days the valve is fully rehydrated. The suturing of membrane layers to form the valve is done with single, double, or more continuous suture material. This form of suturing has great advantages for durability and avoidance of damage to the membrane and can be performed by sewing machines. The attachment points of the leaflet layer to the cuff layer may be reinforced by folding an additional layer of membrane over the attachment point before suturing, this layer being formed of a projected tab of the continuous piece of leaflet membrane. The free edge of the leaflet layer may be straight or curved, and this free edge forming the free edges of the individual leaflets may be contoured in parabolic or curved shape.

Attachment of the Valve Means to the Stent Member

The valve means 200 is then attached to the inner channel of the stent member 100 by suturing the outer surface of the valve means' pericardium material to the stent member. FIG. 7 depicts preferred suture points of one embodiment of the present invention: 3-point fixation or 6-point fixation at each border of the stent. Other fixation schemes can be utilized, such as, by way of non-limiting example, fixation on both borders 18 points at each end following a single plane and 36 fixation points following to adjacent vertical planes. The use of only one plane of fixation points helps prevent systolic collapse of the proximal edge of the valve means. A fold on the border of the pericardium material prevents tearing. The attachment position of the valve is preferably closer to the proximal and wider part of the stent.

The sequence of steps can vary. The pericardium material can be fixed in glutaraldehyde before attachment to the stent or the valve can be formed and then fixed with glutaraldehyde after mounting it in the stent. One observation noted is that the material becomes whiter and apparently increases its elasticity. 1 mm vascular clips keep the cusps coapted while fixing them in glutaraldehyde. The use of metallic clips to keep both cusps adjacent to each other after 24 hours of fixation in glutaraldehyde helps to educate the material and make the primary position of the valve cusps adjacent to each other. After the clips are removed, there are no lesions to the valve.

Different suture materials can be used, including, in a preferred embodiment, Prolene 1-0 to 8-0 and Mersilene 1-0 to 8-0 which is a braided suture.

Implantation of Replacement Heart Valve Device

The replacement heart valve device of the present invention is preferably used in surgical procedures involving the percutaneous and transluminal removal of the diseased or defective heart valve and the percutaneous and transluminal implantation of the new heart valve described above. The defective heart valve is removed by a suitable modality, such as, for example, laser, ultrasound, mechanical, or other suitable forms of delivery of energy, or phacoemulsion, including, but not limited to, laser lithotripsy, mechanical lithotripsy, electrohydraulic lithotripsy, and laser or mechanical ablation. To remove the native heart valve that is being replaced, a guidewire is inserted percutaneously and translu-

11

minally using standard vascular or angiography techniques. The distal end of the guidewire is manipulated to extend through and across the defective heart valve. Then a catheter is advanced distally through the femoral artery to a point proximal to the defective heart valve, between the origin of the coronary artery and the origin of the right subclavian artery. The position of the distal end of catheter can be monitored by observation of radiopaque markers. Collector member is preferably inflated and occludes the aorta at a point between the origin of the coronary artery and the right subclavian artery. Next, a balloon and cutting tool are advanced through the catheter so that the cutting tool and uninflated balloon are distal to the defective heart valve. Optionally an additional step, such as balloon dilatation or athrectomy, may be required to provide a passageway through the heart valve. A catheter is also placed into the coronary sinus via a transjugular puncture. This catheter is used for infusion of blood or cardioplegia solution during the portion of the procedure when the aorta is occluded. The absence of valves in the cardiac venous system allows retrograde flow so that there will be an effluence of fluid from the coronary arteries. This flow of fluid is desired to prevent embolization of material into the coronary arteries during the procedure. Once the cutting tool is in place, the balloon is inflated and flexible shaft is rotated. Once the cutting tool has reached the appropriate rotation speed, the cutting tool is pulled proximally to remove the defective heart valve. The balloon and the cutting tool are spaced apart so that the inflated balloon will be stopped by the perimeter, unremoved portion of the defective heart valve, which will signal the physician that the valve has been removed, as well as protect the heart and aorta from damage from the valve removal device. Once it is determined that the defective heart valve has been removed, the cutting tool is slowed or stopped altogether and the balloon is deflated. The cutting tool and the deflated balloon are pulled proximally through catheter. Then, a catheter containing an artificial heart valve is inserted and the artificial heart valve is placed as described above.

The delivery and implantation system of the replacement artificial heart valve of the present invention percutaneously and transluminally includes a flexible catheter **400** which may be inserted into a vessel of the patient and moved within that vessel as depicted in FIG. **8**. The distal end **410** of the catheter **400**, which is hollow and carries the replacement heart valve device of the present invention in its collapsed configuration, is guided to a site where it is desired to implant the replacement heart valve. The catheter has a pusher member **420** disposed within the catheter lumen **430** and extending from the proximal end **440** of the catheter to the hollow section at the distal end **410** of the catheter. Once the distal end **410** of the catheter is positioned as desired, the pusher mechanism **420** is activated and the distal portion of the replacement heart valve device is pushed out of the catheter and the stent member **100** partially expands. In this position the stent member **100** is restrained so that it doesn't pop out and is held for controlled release, with the potential that the replacement heart valve device can be recovered if there is a problem with the positioning. The catheter **400** is then retracted slightly and the replacement heart valve device is completely pushed out of the catheter **400** and released from the catheter to allow the stent member **100** to fully expand. If the stent member **100** preferably includes two circles of barbs on its outer surface as previously described, the first push and retraction will set one circle of barbs in adjacent tissue and the second push and release of the replacement heart valve device will set the other circle of barbs in adjacent tissue and securely

12

fix the replacement heart valve device in place when the device is released from the catheter.

Alternatively, or in combination with the above, the replacement heart valve device could be positioned over a metallic guidewire that is advanced through the catheter. The replacement heart valve device of the present invention is preferably implanted percutaneously through an aortic passageway to, or near to, the location from which the natural heart valve has been removed. Referring to FIG. **8**, the implantation system comprises a flexible hollow tube catheter **410** with a metallic guide wire **450** disposed within it. The stented valve device is collapsed over the tube and is covered by a moveable sheath **460**. The moveable sheath **460** maintains the stented valve device in the collapsed position. The implantation method comprises the following steps: inserting the replacement heart valve device in the lumen of a central blood vessel via entry through the brachial or femoral artery using a needle or exposing the artery surgically; placing a guide wire **450** through the entry vessel and advancing it to the desired position; advancing dilators over the wire to increase the lumen of the entry site, thereby preparing the artery to receive the heart-valve; and advancing the heart-valve device to the desired place. The stented-valve device is released by pulling the cover sheath **460** of the delivery system allowing the self-expanding stent to achieve its full expansion. A balloon expandable stent can alternately be used to deliver the valve to its desired position. At this point, a pigtail catheter is advanced over the wire and an aortogram is performed to assess the competency of the valve.

Before creation of the valve means and implantation, the patient is studied to determine the architecture of the patient's heart. Useful techniques include fluoroscopy, transesophageal echocardiography, MRI, and angiography. The results of this study will enable the physician to determine the appropriate size for the replacement heart valve.

In one procedure for implantation of the replacement heart valve device of the present invention, the femoral artery of the patient is cannulated using a Cook needle and a standard J wire is advanced into the artery either percutaneously or after surgical exposure of the artery. An 8 F introducer is advanced into the femoral artery over the wire. The J wire is then withdrawn and anticoagulation is started using heparin 60 U/Kg intravenously. Once vascular access is obtained an aortogram is performed for anatomical evaluation. A special wire (Lunderquist or Amplatz superstiff) is advanced into the aortic arch and dilators progressively larger are advanced over the wire, starting with 12 F all the way to 18 F. After this the valve introducer device containing the prosthetic valve device is then inserted and used to transport the replacement valve over a guidewire to the desired position. The stented-valve is released by pulling the cover sheath of the delivery system allowing the self-expanding stent to achieve its full expansion. At this point, a pigtail catheter is advanced over the wire and repeat aortogram is performed to assess the competency of the valve.

When the device is used to treat severe leakage of the aortic valve, the native valve is left in place and the prosthetic stented valve is deployed below the subclavian artery. When the device is used to treat aortic stenosis, first the stenotic valve needs to be opened using either aortic valvuloplasty or cutting and if this procedure induces aortic insufficiency the stented valve is placed to prevent the regurgitation.

Intravascular ultrasound or an angioscope passed intravascularly via either the venous system through the intra-atrial septum across the mitral valve and into the left ventricle or retrograde via the femoral artery would provide the added

13

benefit of allowing constant high definition imaging of the entire procedure and high flow irrigation.

Once the endovascular implantation of the prosthetic valve device is completed in the host, the function of the prosthetic valve device can be monitored by the same methods as used to monitor valve replacements done by open heart surgery. Routine physical examination, periodic echocardiography or angiography can be performed. In contrast to open heart surgery, however, the host requires a short recovery period and can return home within one day of the endovascular procedure. The prosthetic valve device can be used in any patient where bioprosthetic valves are indicated, namely elderly patients with cardiac valve diseases, and patients unable to tolerate open heart procedures or life-long anticoagulation. In addition, with the development of longer-life, flexible, non-thrombogenic synthetic valve alternatives to bioprostheses, the prosthetic valve device will be indicated in all patients where the relative advantages of the life-span, the non-thrombogenic quality, and the ease of insertion of prosthetic valve devices outweigh the disadvantages of mechanical valves. Anticoagulation may be beneficial in certain clinical situations for either short or long term use.

This method of percutaneous endovascular heart-valve replacement, in contrast to open heart surgical procedures, requires only local anesthesia, partial or no cardiac bypass, one to two days hospitalization, and should result in a reduced mortality rate as compared to open heart procedures.

While the present invention has been shown and described herein in what is considered to be a preferred embodiment thereof, illustrating the results and advantages over the prior art obtained through the present invention, the invention is not limited to the specific embodiments described above. Thus, the forms of the invention shown and described herein are to be taken as illustrative and other embodiments may be selected without departing from the spirit and scope of the present invention.

14

What is claimed is:

1. An assembly to treat a native heart valve in a patient, the assembly for use in combination with a guidewire, the assembly comprising:

a prosthetic heart valve including:

a stent member having an inner channel, the stent member collapsible, expandable and configured for transluminal percutaneous delivery, wherein the stent member includes a tubular structure away from a central portion that flares at both ends in a trumpet-like configuration; and

a valve means including two to four individual leaflets made of fixed pericardial tissue, wherein the valve means resides entirely within the inner channel of the stent member, and wherein no reinforcing members reside within the inner channel of the stent member;

a delivery system including a pusher member and a moveable sheath, the pusher member including a guidewire lumen, wherein the pusher member is disposed within a lumen of the moveable sheath, wherein the prosthetic heart valve is collapsed onto the pusher member to reside in a collapsed configuration on the pusher member and is restrained in the collapsed configuration by the moveable sheath, wherein a distal end of the prosthetic heart valve is located at a distal end of the moveable sheath, and wherein the valve means resides entirely within the inner channel of the stent member in said collapsed configuration and is configured to continue to reside entirely within the inner channel of the stent member upon deployment in the patient.

2. The assembly of claim 1, wherein the stent member is self-expanding.

3. The assembly of claim 2, wherein the stent member comprises nitinol.

4. The assembly of claim 1, wherein the stent member includes two circles of barbs on an outer surface of the stent member.

5. The assembly of claim 1, wherein the pusher member includes a controlled release mechanism that can be activated.

* * * * *