



US011253635B2

(12) **United States Patent**
MacEwan

(10) **Patent No.:** **US 11,253,635 B2**
(45) **Date of Patent:** ***Feb. 22, 2022**

(54) **THREE DIMENSIONAL ELECTROSPUN BIOMEDICAL PATCH FOR FACILITATING TISSUE REPAIR**

(71) Applicant: **Washington University**, St. Louis, MO (US)

(72) Inventor: **Matthew R. MacEwan**, St. Louis, MO (US)

(73) Assignee: **Washington University**, St. Louis, MO (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **17/381,792**

(22) Filed: **Jul. 21, 2021**

(65) **Prior Publication Data**

US 2021/0353834 A1 Nov. 18, 2021

Related U.S. Application Data

(60) Continuation of application No. 17/229,226, filed on Apr. 13, 2021, now Pat. No. 11,173,234, which is a (Continued)

(51) **Int. Cl.**

A61L 31/04 (2006.01)

D01D 5/00 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **A61L 31/04** (2013.01); **A61L 15/26** (2013.01); **A61L 15/44** (2013.01); **A61L 15/64** (2013.01);

(Continued)

(58) **Field of Classification Search**

USPC 623/23.72; 427/2.31; 264/466

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,068,703 A 1/1937 Powdermaker

3,280,229 A 10/1966 Simons

(Continued)

FOREIGN PATENT DOCUMENTS

AU 2011268321 B2 10/2015

AU 2012390291 B2 9/2017

(Continued)

OTHER PUBLICATIONS

3rd International Conference on Electrospinning Conference Program dated Aug. 4-7, 2004, www.ceramics.org/electrospin2014.

(Continued)

Primary Examiner — Lynda Salvatore


(74) *Attorney, Agent, or Firm* — Armstrong Teasdale LLP

(57)

ABSTRACT

A three-dimensional electrospun biomedical patch includes a first polymeric scaffold having a first structure of deposited electrospun fibers extending in a plurality of directions in three dimensions to facilitate cellular migration for a first period of time upon application of the biomedical patch to a tissue, wherein the first period of time is less than twelve months, and a second polymeric scaffold having a second structure of deposited electrospun fibers. The second structure of deposited electrospun fibers includes the plurality of deposited electrospun fibers configured to provide structural reinforcement for a second period of time upon application of the three-dimensional electrospun biomedical patch to the tissue wherein the second period of time is less than twelve months. The three-dimensional electrospun biomedical patch is sufficiently pliable and resistant to tearing to enable movement of the three-dimensional electrospun biomedical patch with the tissue.

30 Claims, 12 Drawing Sheets



Related U.S. Application Data

continuation of application No. 16/872,926, filed on May 12, 2020, which is a continuation of application No. 16/540,779, filed on Aug. 14, 2019, now Pat. No. 10,682,444, which is a continuation of application No. 16/131,887, filed on Sep. 14, 2018, now Pat. No. 10,441,685, which is a division of application No. 14/429,976, filed as application No. PCT/US2012/056548 on Sep. 21, 2012, now Pat. No. 10,124,089.

(51) **Int. Cl.**

B29C 48/18 (2019.01)
B32B 5/02 (2006.01)
B32B 5/26 (2006.01)
B32B 7/02 (2019.01)
B32B 7/12 (2006.01)
A61L 27/18 (2006.01)
A61L 27/54 (2006.01)
A61L 27/58 (2006.01)
A61L 15/26 (2006.01)
A61L 15/44 (2006.01)
A61L 15/64 (2006.01)
A61L 27/60 (2006.01)
D04H 1/728 (2012.01)
D04H 3/16 (2006.01)
A61F 13/02 (2006.01)

(52) **U.S. Cl.**

CPC **A61L 27/18** (2013.01); **A61L 27/54** (2013.01); **A61L 27/58** (2013.01); **A61L 27/60** (2013.01); **B29C 48/18** (2019.02); **B32B 5/022** (2013.01); **B32B 5/26** (2013.01); **B32B 7/02** (2013.01); **B32B 7/12** (2013.01); **D01D 5/0007** (2013.01); **D01D 5/0038** (2013.01); **D01D 5/0061** (2013.01); **D01D 5/0076** (2013.01); **D04H 1/728** (2013.01); **D04H 3/16** (2013.01); **A61F 13/02** (2013.01); **A61L 2300/414** (2013.01); **A61L 2400/12** (2013.01); **A61L 2400/18** (2013.01); **A61L 2430/20** (2013.01); **A61L 2430/32** (2013.01); **B32B 2250/20** (2013.01); **B32B 2262/0276** (2013.01); **B32B 2307/518** (2013.01); **B32B 2307/54** (2013.01); **B32B 2307/726** (2013.01); **B32B 2307/7265** (2013.01); **B32B 2556/00** (2013.01); **D10B 2509/00** (2013.01)

(56) **References Cited****U.S. PATENT DOCUMENTS**

3,338,992 A	8/1967	Kinney	5,795,584 A	8/1998	Totakura et al.
3,341,394 A	9/1967	Kinney	5,851,937 A	12/1998	Wu et al.
3,502,763 A	3/1970	Hartmann	5,997,568 A	12/1999	Liu
3,542,615 A	11/1970	Dobo et al.	6,147,135 A	11/2000	Yuan et al.
3,692,618 A	9/1972	Dorschner et al.	6,162,535 A	12/2000	Turkevich et al.
3,740,302 A	6/1973	Soehngen	6,171,338 B1	1/2001	Talja et al.
3,802,817 A	4/1974	Matsuki et al.	6,180,848 B1	1/2001	Flament et al.
3,849,241 A	11/1974	Butin et al.	6,183,670 B1	2/2001	Torobin et al.
3,909,009 A	9/1975	Cvetko et al.	6,265,333 B1	7/2001	Dzenis et al.
4,044,404 A	8/1977	Martin et al.	6,306,424 B1	10/2001	Vyakarnam et al.
4,340,563 A	7/1982	Appel et al.	6,391,060 B1	5/2002	Ory et al.
4,468,428 A	8/1984	Early et al.	6,596,296 B1	7/2003	Nelson et al.
4,738,740 A	4/1988	Pinchuk et al.	6,630,231 B2	10/2003	Perez et al.
4,965,110 A	10/1990	Berry	6,649,807 B2	11/2003	Mizutani
5,024,789 A	6/1991	Berry	6,685,956 B2	2/2004	Chu et al.
5,079,080 A	1/1992	Schwartz	6,689,374 B2	2/2004	Chu et al.
5,306,550 A	4/1994	Nishiyama et al.	6,713,011 B2	3/2004	Chu et al.
5,464,450 A	11/1995	Buscemi et al.	6,753,454 B1	6/2004	Smith et al.
5,591,335 A	1/1997	Barboza et al.	6,790,455 B2	9/2004	Chu et al.
5,626,611 A	5/1997	Liu et al.	6,797,655 B2	9/2004	Rudisill
			6,946,506 B2	9/2005	Bond et al.
			7,134,857 B2	11/2006	Andrady et al.
			7,172,765 B2	2/2007	Chu et al.
			7,192,604 B2	3/2007	Brown et al.
			7,655,070 B1	2/2010	Dallas et al.
			7,759,082 B2	7/2010	Bowlin et al.
			7,799,262 B1	9/2010	Kim
			7,846,466 B2	12/2010	Shea et al.
			7,879,093 B2	2/2011	Wei et al.
			7,981,353 B2	7/2011	Mitchell et al.
			8,066,932 B2	11/2011	Xu
			8,222,166 B2	7/2012	Chu et al.
			8,273,369 B2	9/2012	Moloye-Olabisi et al.
			8,652,215 B2	2/2014	Bellamkonda et al.
			8,728,463 B2	5/2014	Atala et al.
			8,728,817 B2	5/2014	Ogle et al.
			8,809,212 B1	8/2014	Dirk et al.
			8,852,621 B2	10/2014	Patel et al.
			9,074,172 B2	7/2015	Johnson
			9,085,830 B2	7/2015	Mitchell et al.
			9,163,331 B2	10/2015	Atala et al.
			9,168,231 B2	10/2015	Patel et al.
			9,345,486 B2	5/2016	Zhang et al.
			9,393,097 B2	7/2016	McCullen et al.
			9,476,026 B2	10/2016	Arinze et al.
			9,487,893 B2	11/2016	Moore et al.
			9,539,365 B2	1/2017	Kasuga et al.
			9,572,909 B2	2/2017	Simpson et al.
			9,585,666 B2	3/2017	Yu et al.
			9,737,632 B2	8/2017	Johnson et al.
			9,884,027 B2	2/2018	Johnson
			9,938,373 B2	4/2018	Wang et al.
			10,016,464 B2	7/2018	Murphy et al.
			10,080,687 B2	9/2018	MacEwan
			10,124,089 B2	11/2018	MacEwan
			10,149,749 B2	12/2018	MacEwan et al.
			10,166,315 B2	1/2019	Johnson et al.
			10,227,568 B2	3/2019	Johnson
			10,231,821 B2	3/2019	Gabriele et al.
			10,233,427 B2	3/2019	Johnson
			10,239,262 B2	3/2019	Johnson
			10,294,449 B2	5/2019	Johnson
			10,335,154 B2	7/2019	Johnson et al.
			10,363,041 B2	7/2019	Yu et al.
			10,381,672 B2	8/2019	Lee et al.
			10,405,963 B2	9/2019	McAlpine et al.
			10,406,346 B2	9/2019	Scott-Carnell et al.
			10,413,574 B2	9/2019	Fong et al.
			10,420,856 B2	9/2019	Arinze et al.
			10,441,403 B1	10/2019	MacEwan et al.
			10,441,685 B2	10/2019	MacEwan
			10,588,734 B2	3/2020	MacEwan et al.
			10,617,512 B2	4/2020	MacEwan
			10,632,228 B2	4/2020	MacEwan
			10,682,444 B2 *	6/2020	MacEwan A61L 15/26
			10,738,152 B2	8/2020	Wang et al.
			10,888,409 B2	1/2021	MacEwan et al.
			11,000,358 B2	5/2021	MacEwan et al.
			11,096,772 B1	8/2021	MacEwan et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

11,176,234 B2	11/2021	MacEwan et al.	2011/0280919 A1	11/2011	Moloye-Olabisi et al.
2002/0081732 A1	6/2002	Bowlin et al.	2011/0287082 A1	11/2011	Smith et al.
2002/0090725 A1	7/2002	Simpson et al.	2012/0015331 A1	1/2012	Wood et al.
2002/0173213 A1	11/2002	Chu et al.	2012/0029654 A1	2/2012	Xu et al.
2002/0192251 A1	12/2002	Collin	2012/0040581 A1	2/2012	Kim
2003/0004579 A1	1/2003	Rousseau et al.	2012/0123342 A1	5/2012	Andrews et al.
2003/0054035 A1	3/2003	Chu et al.	2012/0165957 A1	6/2012	Everland et al.
2004/0013819 A1	1/2004	Hou et al.	2012/0225039 A1	9/2012	Li et al.
2004/0018226 A1	1/2004	Wnek et al.	2012/0265300 A1	10/2012	Mauck et al.
2004/0037813 A1	2/2004	Simpson et al.	2012/0310260 A1	12/2012	Hamlin et al.
2004/0096532 A1	5/2004	Dubson et al.	2012/0330437 A1	12/2012	El-Kurdi et al.
2004/0102614 A1	5/2004	Islam et al.	2013/0035704 A1	2/2013	Dudai
2005/0104258 A1	5/2005	Lennhoff	2013/0110138 A1	5/2013	Hurtado
2005/0167311 A1	8/2005	Tonsfeldt et al.	2013/0115457 A1	5/2013	Haynie et al.
2005/0222591 A1	10/2005	Gingras et al.	2013/0197663 A1	8/2013	MacEwan et al.
2006/0085063 A1	4/2006	Shastri et al.	2013/0251762 A1	9/2013	Wei et al.
2006/0094320 A1	5/2006	Chen et al.	2013/0338791 A1	12/2013	McCullen et al.
2006/0153904 A1	7/2006	Smith et al.	2014/0030315 A1	1/2014	Johnson
2006/0193578 A1	8/2006	Ouderkirk et al.	2014/0081297 A1	3/2014	Hoke et al.
2006/0014460 A1	9/2006	Isele et al.	2014/0128345 A1	5/2014	Woodrow et al.
2006/0204539 A1	9/2006	Atala et al.	2014/0272225 A1	9/2014	Johnson
2006/0240110 A1	10/2006	Kick et al.	2014/0303727 A1	10/2014	Atlas et al.
2006/0246798 A1	11/2006	Reneker et al.	2014/0322512 A1	10/2014	Pham et al.
2006/0263417 A1	11/2006	Lelkes et al.	2015/0045818 A1	2/2015	Kim et al.
2006/0264140 A1	11/2006	Andrady et al.	2015/0132423 A1	5/2015	Johnson
2007/0073344 A1	3/2007	Jahns et al.	2015/0190285 A1	7/2015	MacEwan
2007/0152378 A1	7/2007	Kim	2015/0250927 A1	9/2015	MacEwan
2007/0155273 A1	7/2007	Chu et al.	2015/0297791 A1	10/2015	Patel et al.
2007/0225631 A1	9/2007	Bowlin et al.	2015/0342719 A1	12/2015	Chen et al.
2007/0269481 A1	11/2007	Li et al.	2016/0022873 A1	1/2016	Besner et al.
2008/0065123 A1	3/2008	Yli-Urpo et al.	2016/0083692 A1	3/2016	Hardy et al.
2008/0112998 A1	5/2008	Wang et al.	2016/0083868 A1	3/2016	Park
2008/0207798 A1	8/2008	Hellring et al.	2016/0136330 A1	5/2016	Benkirane-Jessel et al.
2008/0208358 A1	8/2008	Bellamkonda et al.	2016/0302869 A1	10/2016	Chopra
2008/0220042 A1	9/2008	Hashi et al.	2016/0317706 A1	11/2016	Johnson
2008/0237934 A1	10/2008	Reneker et al.	2017/0095591 A1	4/2017	Zuhaib et al.
2009/0028921 A1	1/2009	Arinzeh	2017/0119886 A1	5/2017	Johnson et al.
2009/0074832 A1	3/2009	Zussman et al.	2017/0182206 A1	6/2017	Johnson et al.
2009/0075354 A1	3/2009	Reneker et al.	2017/0182211 A1	6/2017	Raxworthy et al.
2009/0155326 A1	6/2009	Mack et al.	2017/0319323 A1	11/2017	MacEwan et al.
2009/0162468 A1	6/2009	Barinov et al.	2017/0319742 A1	11/2017	Johnson et al.
2009/0171467 A1	7/2009	Mann et al.	2017/0326270 A1	11/2017	MacEwan
2009/0202616 A1	8/2009	Chong et al.	2018/0116973 A1	5/2018	Jonsson
2009/0214614 A1	8/2009	Everland et al.	2018/0161185 A1	6/2018	Kresslein et al.
2009/0228021 A1	9/2009	Leung	2018/0174367 A1	6/2018	Marom et al.
2009/0317446 A1	12/2009	Tan et al.	2018/0221537 A1	8/2018	Johnson et al.
2010/0003305 A1	1/2010	Pattanaik	2018/0237952 A1	8/2018	Johnson et al.
2010/0047309 A1	2/2010	Lu et al.	2018/0245243 A1	8/2018	Krieger et al.
2010/0061962 A1	3/2010	Li	2018/0263919 A1	9/2018	Hoke et al.
2010/0076377 A1	3/2010	Ehrenreich et al.	2018/0368917 A1	12/2018	Dekel et al.
2010/0092687 A1	4/2010	Sumida et al.	2019/0015563 A1	1/2019	MacEwan
2010/0093093 A1	4/2010	Leong et al.	2019/0021837 A1	1/2019	MacEwan et al.
2010/0119564 A1	5/2010	Kasuga et al.	2019/0054036 A1	2/2019	Johnson et al.
2010/0120115 A1	5/2010	Ogle et al.	2019/0102880 A1	4/2019	Parpara et al.
2010/0166854 A1	7/2010	Kohn et al.	2019/0105128 A1	4/2019	Velazquez et al.
2010/0174368 A1	7/2010	Lynch et al.	2019/0134267 A1	5/2019	Francis et al.
2010/0179659 A1	7/2010	Li et al.	2019/0134570 A1	5/2019	Pintauro et al.
2010/0185219 A1	7/2010	Gertzman et al.	2019/0153398 A1	5/2019	Johnson
2010/0190254 A1	7/2010	Chian et al.	2019/0175786 A1	6/2019	Cohen et al.
2010/0233115 A1	9/2010	Patel et al.	2019/0249127 A1	8/2019	Johnson
2010/0273258 A1	10/2010	Lannutti et al.	2019/0269829 A1	9/2019	Johnson
2010/0291182 A1	11/2010	Palasis et al.	2019/0271098 A1	9/2019	Johnson et al.
2010/0292791 A1	11/2010	Lu et al.	2019/0330419 A1	10/2019	Song et al.
2010/0297208 A1	11/2010	Fry et al.	2019/0328393 A1	11/2019	Yu et al.
2010/0330419 A1	12/2010	Cui et al.	2019/0350688 A1	11/2019	Hurtado et al.
2010/0331980 A1	12/2010	Lee et al.	2019/0365520 A1	12/2019	MacEwan et al.
2011/0087277 A1	4/2011	Vola et al.	2019/0365958 A1	12/2019	MacEwan
2011/0098826 A1	4/2011	Mauck et al.	2019/0374227 A1	12/2019	Johnson et al.
2011/0101571 A1	5/2011	Reneker	2020/0000570 A1	1/2020	MacEwan et al.
2011/0111012 A1	5/2011	Pepper et al.	2020/0060800 A1	2/2020	MacEwan et al.
2011/0150973 A1	6/2011	Bowlin et al.	2020/0197153 A1	6/2020	MacEwan et al.
2011/0152897 A1	6/2011	Bates	2020/0229679 A1	7/2020	Zhao et al.
2011/0174158 A1	7/2011	Walls et al.	2020/0242767 A1	7/2020	Zhao et al.
2011/0180951 A1	7/2011	Teo et al.	2020/0277711 A1	9/2020	Xie
2011/0242310 A1	10/2011	Beebe, Jr. et al.	2020/0390932 A1	12/2020	MacEwan
			2021/0001014 A1*	1/2021	MacEwan A61L 15/26
			2021/0030525 A1	2/2021	MacEwan et al.
			2021/0052362 A1	2/2021	MacEwan et al.
			2021/0228782 A1*	7/2021	MacEwan A61L 15/44

(56)

References Cited**U.S. PATENT DOCUMENTS**

2021/0236691 A1 8/2021 MacEwan
 2021/0267746 A1 9/2021 MacEwan et al.
 2021/0338408 A1 11/2021 MacEwan et al.

FOREIGN PATENT DOCUMENTS

CA 2094908 C 2/2000
 CA 2802482 A1 12/2011
 CA 2386810 C 9/2013
 CN 102260963 A 11/2011
 CN 102691176 A 9/2012
 CN 103599562 A 2/2014
 CN 104894750 A 9/2015
 DE 102014107826 A1 12/2014
 EP 0515522 B1 10/1993
 EP 0571415 B1 7/1995
 EP 0757127 A1 2/1997
 EP 2045375 B1 3/2011
 EP 2358301 8/2011
 EP 2599858 6/2013
 EP 2582868 B1 3/2018
 EP 3508641 B1 8/2020
 EP 2897561 B1 11/2020
 EP 3741896 A1 11/2020
 GB 1286858 A 8/1972
 GB 2181207 A 4/1987
 GB 2195251 A 4/1988
 JP H03161563 A 7/1991
 JP 3487722 B2 1/2004
 JP 3487722 B2 1/2004
 JP 2005534828 A 11/2005
 JP 2006283241 A 10/2006
 JP 2006328562 A 12/2006
 JP 2007303021 A 11/2007
 JP 2008223186 A 9/2008
 JP 2009061109 A 3/2009
 JP 2011509786 A 3/2011
 JP 4769871 B2 9/2011
 JP 4979264 B2 7/2012
 JP 2012528464 A 11/2012
 JP 2013518996 A 5/2013
 JP 2013534979 A 9/2013
 JP 6295258 A 3/2018
 JP 6328672 B2 5/2018
 KR 100439871 B1 7/2004
 KR 20060118937 A 11/2006
 KR 1020070047873 A 5/2007
 KR 101703095 A 10/2013
 SG 186379 A1 1/2013
 SG 11201502207W A 4/2015
 WO 1991001695 A1 2/1991
 WO 2001027365 A1 4/2001
 WO 2002000149 A1 1/2002
 WO 2004016839 A1 2/2004
 WO 2006096791 A2 9/2006
 WO 2006123858 A1 11/2006
 WO 2007086910 A2 8/2007
 WO 2008069760 A1 6/2008
 WO 2009093023 A2 7/2009
 WO 2010041944 A1 4/2010
 WO 2010042651 A1 4/2010
 WO 2010112564 A2 10/2010
 WO 2010138619 A2 12/2010
 WO 2011095141 A1 8/2011
 WO 2011159889 A2 12/2011
 WO 2012080706 A2 6/2012
 WO 2013025819 A2 2/2013
 WO 2013050428 A1 4/2013
 WO 2013078051 A1 5/2013
 WO 2013106822 A1 7/2013
 WO 2014031721 A1 2/2014
 WO 2014046669 A1 3/2014
 WO 2014145864 A1 9/2014
 WO 2014152906 A2 9/2014
 WO 2015048224 A1 4/2015

WO 2015116917 A1 8/2015
 WO 2015153011 A1 10/2015
 WO 2015/157485 10/2015
 WO 2016176559 A1 11/2016
 WO 2017024263 A1 2/2017
 WO 2017035500 A1 3/2017
 WO 2017044982 A1 3/2017
 WO 2017079328 A1 5/2017
 WO 2017196325 A1 11/2017
 WO 2018112203 A1 6/2018
 WO 2018144858 A1 8/2018

OTHER PUBLICATIONS

ASTM Standard F2450-10, "Guide for Assessing Microstructure of Polymeric Scaffolds for Use in Tissue-Engineered Medical Products" ASTM International, West Conshohocken, PA, 10 pages (Mar. 27, 2013).

Barbol et al., "Biocompatibility evaluation of dura mater substitutes in an animal model," *Neurological Research*, 23(8): 813-820 (2001).

Beachley et al., "Polymer nanofibrous structures: Fabrication, biofunctionalization, and cell interactions," *Progress in Polymer Science*, 35(7): 868-892 (2010).

Beheshtkhoo et al., "Fabrication and Properties of Collagen and Polyurethane Polymeric Nanofibers Using Electrospinning Techniques," *Journal of Environmental Treatment Techniques*, 7(4): 802-807 (2019).

Bhattarai et al., "Electrospun chitosa-based nanofibers and their cellular compatibility", *Biomaterials*, 26(31): 6176-6184 (2005).

Bognitzki et al., "Preparation of Fibers with Nanoscaled Morphologies: Electrospinning of Polymer Blends," *Polymer Engineering and Science*, 41(6): 982-989 (2001).

Bognitzki et al., "Nanostructured Fibers via Electrospinning," *Advanced Materials*, 13(1): 70-72 (2001).

Campos et al., "Local Mechanical Properties of Electrospun Fibers Correlate to Their Internal Nanostructure," *NANO Letters*, 13(11): 5056-5062 (2013).

Chakrapani et al., "Electrospinning of Type I Collagen and PCL Nanofibers Using Acetic Acid," *J. Applied Polymer Science*, 125(4): 3221-3227 (2012); Wiley Online Library, Feb. 1, 2012.

Chen et al., "Preparation and characterization of coaxial electrospun thermoplastic polyurethane/collagen compound nanofibers for tissue engineering applications," *Colloids and Surfaces B: Biointerfaces*, 79(2): 315-325 (2010).

Chen et al., "Preparation and Study of TPU/Collagen Complex Nanofiber via Electrospinning," *AATCC Review*, 10(2): 59-63 (2010).

Cheng et al., "Engineering the Microstructure of Electrospun Fibrous Scaffolds by Microtopography," *Biomacromolecules* 14(5): 1349-1360 (2013) doi: 10.1021/bm302000n).

Choi et al., "Formation of interfiber bonding in electrospun poly(etherimide) nanofiber web," *Journal of Materials Science*, 39(4): 1511-1513 (2004).

Cole et al., "A comparative long-term assessment of four soft tissue substitutes," *Aesthetic Surgery Journal*, 31(6): 674-681 (2011).

Cui et al., "Controlled assembly of poly(vinyl pyrrolidone) fibers through an electric-field-assisted electrospinning method," *Applied Physics A*, 103(1): 167-172 (2011).

Davis, et al., "A biodegradable composite artificial tendon," *Journal of Materials Science: Materials in Medicine* 3: 359-364 (1992).

Deitzel et al., "The Effect of Processing Variables on the Morphology of Electrospun Nanofibers and Textiles," *Polymer*, 42(1): 261-272 (2001).

Doshi, et al., "Electrospinning Process and Applications of Electrospun Fibers," *Journal of Electrostatics*, 35: 151-160 (1995).

Dubsky et al., "Nanofibers Prepared by Needleless Electrospinning Technology as Scaffolds for Wound Healing," *J Materials Science: Materials in Medicine*, 23(4): 931-941(2012), DOI: 10.1007/s10856-012-4577-7.

Dzenis et al., "Hierarchical nano-/micromaterials based on electrospun polymer fibers: Predictive models for thermomechanical behavior" *Journal of Computer-Aided Materials Design*, 3: 403-408 (1996).

(56)

References Cited

OTHER PUBLICATIONS

- Dzenis et al., "Polymer Hybrid Nano/Micro Composites," *Proceedings of the American Society for Composites Ninth Technical Conference*, pp. 657-665, 1994.
- Fang et al., "Electrospinning: An Advanced Nanofiber Production Technology." In: H. Niu, H. Zhou and H. Wang (Eds.), *Energy Harvesting Properties of Electrospun Nanofibers* (1st ed. [online], pp. 1-1-1-44). IOP Publishing Ltd. (2020). <https://iopscience.iop.org/book/978-0-7503-2005-4/chapter/bk978-0-7503-2005-4ch1> (Accessed Apr. 6, 2021), doi 10.1088/978-0-7503-2005-4ch1.
- Figallo et al., "Micropatterned biopolymer 3D scaffold for static and dynamic culture of human fibroblasts," *Biotechnology Progress*, 23(1): 210-216 (2007).
- Foy et al., "Allergic reaction to a bovine dural substitute following spinal cord untethering," *Case Report, Journal of Neurosurgery: Pediatrics*, 1(2): 167-169 (2008).
- Gibson et al., "Electrospun Fiber Mats: Transport Properties," *AIChE Journal*, 45(1): 190-195 (1999).
- Huang et al., "Generation of Synthetic Elastin-Mimetic Small Diameter Fibers and Fiber Networks," *Macromolecules* 33(8): 2989-2997 (2000).
- Jaeger et al., "Electrospinning of Ultra-Thin Polymer Fibers," *Macromolecular Symposia*, 127(1): 141-150 (1998).
- Khil et al., "Novel Fabricated Matrix Via Electrospinning for Tissue Engineering," *Journal of Biomedical Materials Research, Part B, Applied Biomaterials*, 72B(1): 117-124 (2004), <https://doi.org/10.1002/jbm.b.30122>.
- Kumar et al., "Nanofibers: Effective Generation by Electrospinning and Their Applications," *Journal of Nanoscience and Nanotechnology*, 12(1): 1-25 (2012).
- Li et al., "Direct Fabrication of Composite and Ceramic Hollow Nanofibers by Electrospinning" *Nano Letters*, 4(5) 933-938 (2004).
- Li, et al., "Electrospinning Nanofibers as Uniaxially Aligned Arrays and Layer-by-Layer Stacked Films" *Advanced Materials*, 16(4): 361-366 (2004).
- Li et al., "Electrospinning of Nanofibers: Reinventing the Wheel?" *Advanced Materials*, 16(14): 1151-1170 (2004).
- Li, et al., "Electrospinning of Polymeric and Ceramic Nanofibers as Uniaxially Aligned Arrays" *Nano Letters*, 3(8): 1167-1171 (2003).
- Liu et al., "Tensile Mechanics of Electrospun Multiwalled Nanotube/Poly(methyl methacrylate) Nanofibers," *Advanced Materials*, 19(9): 1228-1233 (2007).
- Liu et al., "Electrospun Fibrous Mats on Lithographically Micropatterned Collectors to Control Cellular Behaviors," *Langmuir* 28(49): 17134-17142 (2012), doi: 10.1021/la303490x.
- Madhugiri et al., "Electrospun MEH-PPV/SBA-15 Composite Nanofibers Using a Dual Syringe Method," *J. American Chemical Society*, 125(47): 14531-14538 (2003).
- Martinez-Lage et al., "Accidental transmission of Creutzfeldt-Jakob disease by dural cadaveric grafts" *Journal of Neurology, Neurosurgery & Psychiatry*, 57(9): 1091-1094 (1994).
- McMillan et al., "Small diameter poro poly (ϵ -caprolactone) films enhance adhesion and growth of human cultured epidermal keratinocyte and dermal fibroblast cells," *Tissue Engineering*, 13(4): 789-798 (2007).
- Mi, Fwu-Log et al., "Asymmetric chitosan membranes prepared by dry/wet phase separation: a new type of wound dressing for controlled antibacterial release," *Journal of Membrane Science*, 212(1-2): 237-254 (2003).
- Norris et al., "Electrostatic Fabrication of Ultrafine Conducting Fibers: Polyaniline/Polyethylene Oxide Blends" *Synthetic Metals* 114(2): 109-114 (2000).
- Park et al., "Apparat for Preparing Electrospun Nanofibers: Designing and Electrospinning process for Nanofiber Fabrication," *Polymer International*, 56(11): 1361-1366 (2007).
- Pham et al., "Electrospun poly (ϵ -caprolactone) microfiber and multilayer nanofiber/microfiber scaffold: characterization of scaffolds and measurement of cellular infiltration," *Biomacromolecules*, 7(10): 2796-2805 (2006).
- Pham et al., "Electrospinning of Polymeric Nanofibers for Tissue Engineering Applications: A Review," *Tissue Engineering*, 12(5): 1197-1211 (2006).
- Rieger et al., "Designing Electrospun Nanofiber Mats to Promote Wound Healing—A Review," *J. Materials Chemistry B*, 1(36): 4531-4541 (2013).
- Shin et al., "Electrospun PLGA nanofiber scaffolds for articular cartilage reconstruction: mechanical stability, degradation and cellular responses under mechanical stimulation in vitro," *Journal of Biomaterials Science, Polymer Edition*, 17(1-2): 103-119 (2006).
- Subbiah et al., "Electrospinning of Nanofibers," *J. of Applied Polymer Science*, 96(2): 557-569 (2005).
- Tan et al., "Tensile test of a single nanofiber using an atomic force microscope tip," *Applied Physics Letters*, 86(7): 073115-1:3 (2004).
- Teo et al., "Electrospun scaffold tailored for tissue-specific extracellular matrix," *Biotechnology Journal*, 1(9): 918-929 (2006).
- Thomas et al., "Electrospun bioactive nanocomposite scaffolds of polycaprolactone and nanohydroxyapatite for bone tissue engineering," *Journal of Nanoscience Nanotechnology*, 6(2): 487-93 (2006).
- Tormala, et al., "Ultra-High-Strength absorbable self-reinforced polyglycolide (SR-PGA) composite rods for internal fixation of bone fractures: In vitro and in vivo study" *Journal of Biomedical Materials Research*, 25(1): 1-22 (1991).
- Valizadeh et al., "Electrospinning and Electrospun Nanofibres," *IET Nanobiotechnology*, 8(2): 83-92 (2014).
- Vaz et al., "Design of scaffold for blood vessel tissue engineering using a multiple-layering electrospinning technique," *Acta Biomaterialia*, 1(5): 572-582 (2005).
- Wikipedia, "Polyhydroxyethylmethacrylate," downloaded on Dec. 18, 2019 downloaded from <https://en.wikipedia.org/wiki/Polyhydroxyethylmethacrylate> (3 pages).
- Wise, Histologic proof that acellular dermal matrices (ADM)-Enduragen DermaMatrix and DuraMatrix-are not repopulated or nonviable and that AlloDerm may be repopulated but degraded synchronously, *Aesthetic Surgery Journal*, 32(3): 355-358 (2012).
- Xie et al., "Radially Aligned Electrospun Nanofibers as Dural Substitutes for Wound Closure and Tissue Regeneration Applications," *ACS Nano*, 4(9): 5027-5036 (2010).
- Xie, et al., "Conductive core-sheath nanofibers and their potential applications in neural tissue engineering," *Adv Funct Mater*, 19(14): 2312-2318 (2009).
- Xie et al., "Neurites outgrowth on nanofiber scaffolds with different orders, structures, and surface properties," *ACS Nano*, 3(5): 1151-1159 (2009).
- Xie et al., "Putting electrospun nanofibers to work for biomedical research," *Macromol Rapid Commun.*, 29(22): 1775-1792 (2008).
- Yarin, et al., "Taylor Cone and Jetting from Liquid Driplets in Electrospinning of Nanofibers," *Journal of Applied Physics*, 90(9): 4836-4846 (2001) <https://doi.org/10.1063/1.1408260>; College of Polymer Science and Polymer Engineering. 85 (2001). https://ideaexchange.uakron.edu/polymer_ideas/85.
- Zerris et al., "Repair of the dura mater with processed collagen devices," *Journal of Biomedical Materials Research Part B: Applied Biomaterials*, 83B(2): 580-588 (2007).
- Zong et al., "Structure and process relationship of electrospun bioabsorbable nanofiber membranes," *Polymer*, 43(16): 4403-4412 (2002).
- Australian Examination Report No. 1 issued for Application No. 2012390291 dated May 31, 2017 (4 pages).
- Australian Examination Report issued for Application No. 2011268321, dated Apr. 17, 2015 (4 pages).
- Australian Examination Report No. 1 issued for Application No. 2017232208 dated Jan. 8, 2018 (4 pages).
- Australian Examination Report No. 1 issued for Application No. 2016406314 dated Oct. 29, 2020 (4 pages).
- Australian Examination Report No. 2 issued for Application No. 2016406314 dated Mar. 12, 2021 (3 pages).
- Brazilian Technical Report for related Application No. 112012032169-2, dated Feb. 20, 2019 (4 pages).
- Brazilian Technical Report for related Application No. BR112015006301-2, dated Oct. 15, 2020, 5 pages.
- Canadian Examiner's Report issued for Application No. 2,885,682, dated Jun. 4, 2018 (5 pages).

(56)

References Cited**OTHER PUBLICATIONS**

- Chinese Examiner's Report Issued for Application No. 201680087078.9, dated Jan. 20, 2021 with translation (28 pages).
- European Extended Search Report issued for Application No. 11796426.2, dated Mar. 27, 2014 (6 pages).
- European Examination Report issued for Application No. 12884789.4 dated Feb. 13, 2018 (5 pages).
- European Partial Search Report issued for Application No. 12884789.4, dated Feb. 29, 2016 (8 pages).
- European Extended Search Report issued for Application No. 12884789.4, dated Jun. 16, 2016 (12 pages).
- European Search Report issued for Application No. 16901840.5, dated Dec. 2, 2019 (15 pages).
- European Search Report and Written Opinion for U.S. Appl. No. 18164340, dated May 17, 2019, (5 pages).
- European Search Report and Written Opinion for application No. EP20175280.5, dated Sep. 11, 2020 (8 pages).
- GCC Examination Report in Application No. 2017-33397, dated Apr. 15, 2019 (4 pages).
- Indian Examination Report issued for Application No. 11141/DELNP/2012, dated Jun. 21, 2018 (7 pages).
- Indian First Examination Report for Application No. 2299/DELNP/2015, dated Oct. 24, 2019, (6 pages) English translation.
- Japanese Office action issued for Application No. 2013-515511, dated Oct. 28, 2014 (1 page).
- Japanese Office translation issued for Application No. 2015-533026, dated Jun. 27, 2017 (4 pages).
- Japanese Office Action Summary issued for Application No. 2015-533026, dated Oct. 18, 2016 (5 pages).
- PCT International Search Report and Written Opinion issued for Application No. PCT/2012/056548, dated Apr. 26, 2013 (12 pages).
- PCT International Search Report in International Application No. PCT/16/32001, dated Aug. 11, 2016 (1 page).
- PCT International Search Report and Written Opinion issued for Application No. PCT/2011/040691, dated Feb. 24, 2012 (14 pages).
- PCT International Preliminary Report on Patentability for PCT/2011/040691, dated Dec. 19, 2012 (9 pages).
- Singapore Search Report issued for Application No. 201209288.8, dated May 15, 2014 (17 pages).
- Singapore Search and Examination Report for 2012092888, dated Jan. 30, 2015 (8 pages).
- Singapore Examination Report issued for Application No. 11201502207W, dated Jun. 13, 2017 (8 pages).
- Declaration of Gary E. Wnek, Ph.D. in Support of Petition for Inter Partes Review of U.S. Pat. No. 10,632,228 dated Jan. 2021.
- Petition for Inter Partes Review of U.S. Pat. No. 10,632,228, dated May 28, 2021 (91 pages).
- Chinese Second Office Action Issued for Application No. 201680087078.9, dated Jul. 14, 2021 with translation (23 pages).
- Merriam-Webster "Fiber" Definition downloaded from <https://www.merriam-webster.com/dictionary/fiber> on Jul. 11, 2021.
- Australian Examination Report No. 3 issued for Application No. 2016406314 dated Jul. 5, 2021 (4 pages).
- U.S. Appl. No. 62/154,286, filed Apr. 29, 2015, Johnson.
- Boland et al., "Tissue Engineering Scaffolds," Encyclopedia of Biomaterials and Biomedical Engineering 1: 1630-1638 (2004), doi: 10.1081/E-EBBE-120005552.
- Boland et al., "Tailoring Tissue Engineering Scaffolds Using Electrostatic Proceedings Techniques: A Study of Poly(Glycolic acid) Electrospinning," Journal of Macromolecular Science 38:1231-1243 (2001), doi: 10.1081/MA-100108380.
- Chen et al., "Electrospun 3D Fibrous Scaffolds for Chronic Wound Repair," 2016, Materials 9(272):1-12.
- Chong et al., "Evaluation of electrospun PCL/gelatin nanofibrous scaffold for wound healing and layered dermal reconstruction," Acta Biomaterialia 3:321-330 (2007) doi: 10.1016/j.actbio.2007.10.002 (2007).
- Clark et al., "Investigation of the Effect of Cell Seeding on Neotissue Formation in a Tissue Engineered Trachea," J. Pediatric Surgery, 51(1): 49-55 (2016).
- Defendants' Initial Invalidity Contentions in Civil Action No. 20-980-CFC-JLH dated Nov. 4, 2021 (618 pages).
- Dempsey et al., "Micropatterning of Electrospun Polyurethane Fibers Through Control of Surface Topography," Macromolecular Materials and Engineering 295: 990-994 (2020), doi: 10.1002/mame.201000152.
- Dhandayuthapani et al., "Polymeric Scaffolds in Tissue Engineering Application: A Review" 2011, International Journal of Polymer Science 2011, Article ID 290602, 19 pages.
- Diaz et al., "Fabrication of structured micro and nanofibers by coaxial electrospinning," Journal of Physics, Conference Series 127: 1-8 (2008), doi: 10.1088/1742-6596/127/1/012008.
- Ding et al., "Fabrication of blend biodegradable nanofibrous nonwoven mats via multi-jet electrospinning," Polymer 45: 1895-1902 (2004), doi: 10.1016/j.polymer.2004.01.026.
- European Office Action for application No. 16901840.5, dated Sep. 10, 2021 (9 pages).
- Fridrikh, et al., "Controlling the Fiber Diameter during Electrospinning," The American Physical Society, 90(14): 144502-1 to 144502-4 (2003).
- Grafe et al., "Nanofiber Webs from Electrospinning," Nonwovens in Filtration—Fifth International Conference (2003).
- Huang et al., "A review on polymer nanofibers by electrospinning and their applications in nanocomposites," Composites Science and Technology 63: 2223-2253 (2003), doi: 10.1016/S0266-3538(03)00178-7.
- Indian First Examination Report for IN Application No. 201817046790, dated Sep. 29, 2021, 6 pages.
- Ju et al., "Bilayered scaffold for engineering cellularized blood vessels," Biomaterials 31: 4313-4321 (2010), doi: 10.1016/j.biomaterials.2010.02.002.
- Kenawy et al., "Release of tetracycline hydrochloride from electrospun poly(ethylene-co-vinylacetate), poly(lactic acid), and a blend," Journal of Controlled Release 81: 57-64 (2002), doi: 10.1016/S0168-3659(02)00041-X.
- Kidoaki et al., "Mesoscopic spatial designs of nano—and microfiber meshes for tissue-engineering matrix and scaffold based on newly devised multilayering and mixing electrospinning techniques," Biomaterials 26: 37-46 (2005), doi: 10.1016/j.biomaterials.2004.01.063.
- Le et al., "Engineering a Biocompatible Scaffold with Either Micrometre or Nanometre Scale Surface Topography for Promoting Protein Adsorption and Cellular Response," International Journal of Biomaterials 2013: 1-16 (2013), doi: 10.1155/2013/782549.
- Lee et al., "Development of a composite vascular scaffolding system that withstands physiological vascular conditions," Biomaterials 29: 2891-2898 (2008), doi: 10.1016/j.biomaterials.2008.03.032.
- Manavitehrani et al., "Biomedical Applications of Biodegradable Polyesters" 2016, Polymers 8(20): 1-32.
- McClure et al., "The use of air-flow impedance to control fiber deposition patterns during electrospinning," Biomaterials 33: 771-779 (2012), doi: 10.1016/j.biomaterials.2011.10.011.
- Murthy et al., "Biodegradation of Polymers," Polymer Science: A Comprehensive Reference, 9: 547-560 (2012).
- Pepper et al., "Factors Influencing Poor Outcomes in Synthetic Tissue-Engineered Tracheal Replacement" Otolaryngology-Head and Neck Surgery, 161(3): 458-467 (2019).
- Ramakrishna et al., "Electrospun nanofibers: solving global issues," Materials Today 9: 40-50 (2006), doi: 10.1016/S1369-7021(06)71389-X.
- Schneider et al., "Influence of pH on Wound-healing: a New Perspective for Wound-therapy" 2007 Arch. Dermatol. Res. 298:413-420.
- Shin et al., "Experimental characterization of electrospinning: the electrically forced jet and instabilities" Polymer, 42: 9955-9967 (2001).
- Smith et al., "Suture-reinforced electrospun polydioxanone-elastin small-diameter tubes for use in vascular tissue engineering: a feasibility study," Acta Biomaterialia 4: 58-66 (2008), doi: 10.1016/j.actbio.2007.08.001.

(56)

References Cited

OTHER PUBLICATIONS

Stitzel et al., "Arterial Smooth Muscle Cell Proliferation on a Novel Biomimicking, Biodegradable Vascular Graft Scaffold," *Journal of Biomaterials Applications* 16: 22-33 (2001), doi: 10.1106/U2UU-M9QH-Y0BB-5GYL.

Wikipedia, "Polyhydroxyethylmethacrylate," downloaded Sep. 9, 2020 from <https://en.wikipedia.org/wiki/Polyhydroxyethylmethacrylate> (2 pages).

Wulkersdorfer, "Bimodal Porous Scaffolds by Sequential Electrospinning of Poly(glycolic acid) with Sucrose Particles," *International Journal of Polymer Science* 2010: 1-9 (2010), doi: 10.1155/2010/436178.

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11

506




FIG. 12

508



FIG. 13




FIG. 14




FIG. 15





FIG. 16



THREE DIMENSIONAL ELECTROSPUN BIOMEDICAL PATCH FOR FACILITATING TISSUE REPAIR

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 17/229,226, filed Apr. 13, 2021, which is a continuation of U.S. patent application Ser. No. 16/872,926, filed May 12, 2020, which is a continuation of U.S. patent application Ser. No. 16/540,779, now U.S. Pat. No. 10,682,444, filed Aug. 14, 2019, which is a continuation of U.S. patent application Ser. No. 16/131,887, now U.S. Pat. No. 10,441,685, filed Sep. 14, 2018, which is a divisional of U.S. patent application Ser. No. 14/429,976, now U.S. Pat. No. 10,124,089, filed Mar. 20, 2015, which are incorporated herein in their entirety. U.S. patent application Ser. No. 14/429,976 is a U.S. National Phase Patent Application of International Application Serial Number PCT/US2012/056548, filed Sep. 21, 2012, which is incorporated herein in its entirety.

BACKGROUND

Numerous pathological conditions and surgical procedures result in substantial defects in a variety of organs, tissues, and anatomical structures. In the majority of such cases, surgeons and physicians are required to repair such defects utilizing specialized types of surgical meshes, materials, and/or scaffolds. Unfortunately, the in vivo performance of known surgical materials is negatively impacted by a number of limiting factors. For instance, existing synthetic surgical meshes typically result in excessive fibrosis or scarification leading to poor tissue integration and increased risk of post-operative pain. Simultaneously, known biologic materials may induce strong immune reactions and aberrant tissue ingrowth which negatively impact patient outcomes. Additionally, existing synthetic surgical meshes can create scarification, post-operative pain, limited mobility, limited range of motion, adhesions, infections, erosion, poor biomechanical properties, and/or poor intraoperative handling.

Nanofabricated or nanofiber meshes or materials composed of reabsorbable polymer fibers tens to thousands of times smaller than individual human cells have recently been proposed as a unique substrate for implantable surgical meshes and materials. Generally, existing nanofiber materials tend to possess suboptimal mechanical performance compared to known surgical meshes. Existing nanofiber materials do not possess the tensile strength, tear resistance, and burst strength needed for numerous surgical applications or for basic intraoperative handling prior to in vivo placement. To combat this deficiency, known meshes are formed using higher fiber densities as a means of improving mechanical strength. Yet, utilization of such high-density meshes can decrease effective cellular ingrowth into the mesh, decrease mesh integration with native tissue, and reduce the biocompatibility of the polymeric implant. As a result, nanofiber materials with increased thickness and/or strength and favorable cellular and/or tissue integration and biocompatibility is needed as well as a method for producing nanofiber materials.

SUMMARY

A three-dimensional electrospun nanofiber scaffold for use in repairing a defect in a tissue substrate is provided. The

three-dimensional electrospun nanofiber scaffold includes a first layer formed by a first plurality of electrospun polymeric fibers and a second layer formed by a second plurality of electrospun polymeric fibers. The second layer is coupled to the first layer using a coupling process and includes a plurality of varying densities formed by the second plurality of electrospun polymeric fibers. The first and second layers are configured to degrade via hydrolysis after at least one of a predetermined time or an environmental condition. The three-dimensional electrospun nanofiber scaffold is configured to be applied to the tissue substrate containing the defect.

A three-dimensional electrospun nanofiber scaffold for use in repairing a defect in a tissue substrate is provided. The three-dimensional electrospun nanofiber scaffold includes a first plurality of electrospun polymeric fibers and a second plurality of electrospun polymeric fibers. The second plurality of electrospun polymeric fibers are coupled to the first plurality of electrospun polymeric fibers using a coupling process and form a plurality of varying densities within the three-dimensional electrospun nanofiber scaffold. The first plurality of electrospun polymeric fibers and the second plurality of electrospun polymeric fibers are configured to separate after at least one of a predetermined time or an environmental condition. The three-dimensional electrospun nanofiber scaffold is configured to be applied to the tissue substrate containing the defect.

A biomedical patch for use in repairing a defect in a tissue substrate is provided. The biomedical patch includes a first plurality of electrospun polymeric fibers and a second plurality of electrospun polymeric fibers. The second plurality of electrospun polymeric fibers are coupled to the first plurality of electrospun polymeric fibers using a coupling process and form a plurality of varying densities within the biomedical patch. The first plurality of electrospun polymeric fibers and the second plurality of electrospun polymeric fibers are configured to separate after at least one of a predetermined time or an environmental condition. The biomedical patch is configured to be applied to the tissue substrate containing the defect.

BRIEF DESCRIPTION OF THE DRAWINGS

The embodiments described herein may be better understood by referring to the following description in conjunction with the accompanying drawings.

FIG. 1 is a diagram illustrating an electrospinning system for producing a structure of spatially arranged fibers.

FIG. 2 is a diagram of a collector removed from the electrospinning system of FIG. 1 and having a plurality of fibers deposited thereon forming a patch.

FIG. 3 is an illustration of a biomedical patch including a plurality of spatially arranged electrospun fibers deposited on a collector shown in FIG. 1.

FIG. 4 is another illustration of a biomedical patch including a plurality of spatially arranged electrospun fibers deposited on a collector shown in FIG. 1.

FIG. 5 is an illustration of a solid fiber spinneret shown in FIG. 1.

FIG. 6 is an illustration of a co-axial fiber spinneret shown in FIG. 1.

FIG. 7 is an illustration of a multi-layer biomedical patch.

FIG. 8 is an illustration of a delamination of patches, such as the patch shown in FIG. 7, using various fusion strengths over time.

FIGS. 9 and 10 are histological cross-sections of regenerated dura repaired with multi-laminar nanofiber material such as a patch shown in FIG. 8.

FIGS. 11 and 12 are histological cross-sections of regenerated dura repaired with multi-laminar nanofiber material such as a patch shown in FIG. 8.

FIG. 13 is an illustration of a delamination of patches, such as the patch shown in FIG. 7, using various fusion methods and strengths over time.

FIG. 14 is a flowchart of an exemplary method 700 for producing a structure of spatially arranged fibers using system 100 shown in FIG. 1.

FIG. 15 is a flowchart of an exemplary method 750 for fusing or coupling together structures or patch layers produced by method 700 shown in FIG. 14.

FIG. 16 is a flowchart of an exemplary method 800 for repairing a defect in a biological tissue using the structures produced by methods 700 and 750 shown in FIGS. 14 and 15.

DETAILED DESCRIPTION

Embodiments provided herein facilitate repairing biological tissue or reinforcing biomedical material with the use of a biomedical patch including a plurality of fibers. Such fibers may have a very small cross-sectional diameter (e.g., from 1-3000 nanometers) and, accordingly, may be referred to as nanofibers and/or microfibers. While biomedical patches are described herein with reference to dura mater and use as a surgical mesh, embodiments described may be applied to any biological tissue. Moreover, although described as biomedical patches, structures with aligned fibers may be used for other purposes. Accordingly, embodiments described are not limited to biomedical patches.

In operation, biomedical patches provided herein facilitate cell growth, provide reinforcement, and may be referred to as “membranes,” “scaffolds,” “matrices,” “meshes,” “implants,” or “substrates.” Biomedical patches with varying densities, as described herein, may promote significantly faster healing and/or regeneration of tissue such as the dura mater than existing patches constructed using conventional designs.

Dura mater is a membranous connective tissue comprising the outermost layer of the meninges surrounding the brain and spinal cord, which covers and supports the dural sinuses. Surgical meshes are often needed during neurosurgical, orthopedic, or reconstructive surgical procedures to repair, expand, reinforce, or replace the incised, damaged, or resected dura mater.

Although many efforts have been made, the challenge to develop a suitable surgical mesh for dural repair has been met with limited success. Autografts (e.g., fascia lata, temporalis fascia, and pericranium) are preferable because they do not provoke severe inflammatory or immunologic reactions. Potential drawbacks of autografts include the difficulty in achieving a watertight closure, formation of scar tissue, insufficient availability of graft materials to close large dural defects, increased risk of infection, donor site morbidity, and the need for an additional operative site. Allografts and xenograft materials are often associated with adverse effects such as graft dissolution, encapsulation, foreign body reaction, immunological reaction, contracture, scarring, adhesion formation, and toxicity-induced side effects from immunosuppressive regimens. Lyophilized human dura mater as a dural substitute has also been reported as a source of transmissible diseases, specifically involving prions, such as Creutzfeldt-Jakob disease.

In terms of synthetic surgical mesh materials, non-absorbable synthetic polymers, such as silicone and expanded polytetrafluoroethylene (ePTFE), often cause serious complications that may include induction of granulation tissue formation due to their chronic stimulation of the foreign body response. Natural absorbable polymers, including collagen, fibrin, and cellulose, may present a risk of infection and disease transmission. As a result, synthetic absorbable polymers such as poly (3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV), poly (lactic acid) (PLA), polyglycolic acid (PGA), poly (lactic-co-glycolic acid) (PLGA), PLA-PCL-PGA ternary copolymers, and hydroxyethylmethacrylate hydrogels have recently attracted attention as biodegradable implant materials for dural repair. Methods and systems described herein may be practiced with these materials and/or any biomedical polymer whether the polymer is non-absorbable or absorbable, or synthetic in origin.

In order to facilitate successful regeneration and/or repair of the dura mater following surgery, a synthetic surgical mesh or biomedical patch should promote: i) adhesion of dural fibroblasts (the primary cell type present in the dura) to the surface of the biomedical patch; ii) migration of dural fibroblasts from the periphery of the biomedical patch into the center of the patch; iii) reinforcement or replacement of existing tissues; iv) minimal immune response; v) water tight closure of the dural membrane/dura mater; vi) mechanical support of the native dural post-operatively and during tissue regeneration/neoduralization; vii) rapid closure of the dural defect; and viii) increased ease of use.

Electrospinning is an enabling technique which can produce nanoscale fibers from a large number of polymers. The electrospun nanofibers are typically collected as a randomly-oriented, nonwoven mat. Uniaxially or radially aligned arrays of nanofibers can also be obtained under certain conditions. However, traditional nanofiber scaffolds may lack the optimal mechanical and biological properties necessary for some biomedical or surgical applications post-operatively.

In order to increase the strength of nanofiber scaffolds, custom fabrication of scaffolds into particular patterns would be highly advantageous. Additionally, multiple layers of nanofiber materials fused/coupled together in a manner that allows for a purposeful degradation of the layers can also provide strength while allowing for cellular penetration and/or tissue integration.

Many polymers are available for use in electrospinning. In some embodiments described herein, nanofibers for dura substitutes are produced as the electrospun polymer from poly (ϵ -caprolactone) (PCL), an FDA approved, semicrystalline polyester that can degrade via hydrolysis of its ester linkages under physiological conditions with nontoxic degradation products. This polymer has been extensively utilized and studied in the human body as a material for fabrication of drug delivery carriers, sutures, or adhesion barriers. As described herein, electrospun PCL nanofibers may be used to generate scaffolds that are useful as surgical meshes.

Embodiments provided herein facilitate producing a novel type of artificial tissue substitute including a polymeric nanofiber material, which is formed through a novel method of electrospinning. This polymeric material includes non-woven nanofibers (e.g., fibers having a diameter of 1-3000 nanometers) which are arranged or organized and aligned into patterns both within and across a material sheet.

FIG. 1 is a diagram illustrating a perspective view of an exemplary electrospinning system 100 for producing a structure of spatially arranged or organized fibers. System 100

5

includes a collector **105** with a predetermined pattern **110** including a plurality of reinforcement features **112**. System **100** also includes a spinneret **120**.

System **100** is configured to create an electric potential between one or more collectors **105** and one or more spinnerets **120**. In one embodiment, collector **105** and features **112** are configured to be electrically charged at a first amplitude and/or polarity. For example, collector **105** and features **112** may be electrically coupled to one or more power supplies **130** via one or more conductors **135**. Power supply **130** is configured to charge collector **105** and features **112** at the first amplitude and/or polarity via conductor **135**.

In the embodiment illustrated in FIG. 1, collector **105** includes pattern **110** that is a grid pattern formed by features **112** such that collector **105** is substantially rectangular. In other embodiments, collector **105** may have any shape including, but not limited to, circular, elliptical, ovalar, square, and/or triangular. In one embodiment, features **112** include ribs **114**, seams **116**, and surfaces **118** configured to receive and/or collect polymer fibers. In one embodiment, rib **114** is substantially cylindrical and has a circumference between 5 μ m-100 cm, seam **116** is substantially rectangular having a thickness between 5 μ m-100 cm, and surface **118** is a filling of a void or feature space **119** formed between ribs **114** and/or seams **116**. In one embodiment, surface has a thickness between 5 μ m-10 cm. In the exemplary embodiment, features **112** are made fabricated from at least a portion of metallic substance, including, but not limited to steel, aluminum, tin, copper, silver, gold, platinum, and any alloy or mixture thereof. In one embodiment, features **112** include a coating applied to collector **105**. Coatings can include, but are not limited to anodization, chemical coatings, material coatings (conductive or non-conductive), and gradient coatings that facilitate the creation of continuous gradients of fibers. However, it should be noted that features **112** (e.g., ribs **114**, seams **116**, and surface **118**) can have any shape and be fabricated from any material that facilitates producing patches as disclosed herein.

In the exemplary embodiment, pattern **110** is formed by spatially organizing features **112**. In one embodiment, features **112** (e.g., ribs **114** and seams **116**) are interconnected at nodes **115** such that a feature space **119** is formed between features **112** in the range of 10 μ m and 10 cm. In one embodiment, pattern **110** includes a plurality of spaces **119** such that multiple varying distances are formed between features **112**. It should be noted that pattern can be formed to be symmetrical, repeating, and asymmetrical. In the exemplary embodiment, the shape of collector **105** enables the biomedical patch formed on collector to include additional support and/or reinforcement properties. Such additional support and/or reinforcement properties are achieved by creating high density fiber deposition areas on charged features **112** and having low density fiber deposition areas over feature spaces **119**.

For example, a diamond shaped collector **105** including a diamond shaped array pattern **110** enables a diamond-shaped patch to be produced on the diamond shaped collector **105** to have different mechanical properties from a rectangular-shaped or a circular-shaped patch such as, but not limited to, tensile strength, tear resistance, terminal strain, failure mechanisms or rates, and/or controlled anisotropic properties, such as greater strength in one axis relative to another.

In one embodiment, pattern **110** defines a collector plane **127** and spinneret **120** is orthogonally offset from the collector plane **127** at a variable distance. For example, spinneret **120** may be orthogonally offset from the collector plane **127** at a distance of 50 micrometers to 100 centime-

6

ters. Alternatively, spinneret **120** can be offset from collector **105** in any manner that facilitates creating patches as described herein, including but not limited to, horizontal and diagonal or skew.

Spinneret **120** is configured to dispense a polymer **140** while electrically charged at a second amplitude and/or polarity opposite the first amplitude and/or polarity. As shown in FIG. 1, spinneret **120** is electrically coupled to one or more power supplies **130** by one or more conductors **145**. Power supply **130** is configured to charge one or more spinnerets **120** at the second amplitude and/or polarity via conductor **145**. In some embodiments, power supplies **130** provides a direct current and/or static or time variant voltage (e.g., between 1-50 kilovolts). In one embodiment, conductor **145** is charged positively, and collector **105** is also charged positively. In all embodiments, power supply **130** is configured to allow adjustment of a current, a voltage, and/or a power.

In one embodiment, spinneret **120** is coupled to a dispensing mechanism **150** containing polymer **140** in a liquid solution form. In such an embodiment, dispensing mechanism **150** is operated manually by a dispensing pump **155**. Alternatively, dispensing mechanism **150** can be operated automatically with any mechanism configured to dispense nanofibers as described herein. In the exemplary embodiment, spinneret **120** includes a metallic needle having an aperture between 10 micrometers and 3 millimeters in diameter for dispensing nanofibers.

As dispensing mechanism **150** pressurizes polymer **140**, spinneret **120** dispenses polymer **140** as a jet or stream **160**. In one embodiment, stream **160** is dispensed in a horizontal or sideways stream from spinneret **120**. Stream **160** has a diameter approximately equal to the aperture diameter of spinneret **120**. Stream **160** descends toward collector **105** forming a Taylor cone. For example, stream **160** may fall downward under the influence of gravity and/or may be attracted downward by charge distributed on the fibers and on features **112**. As stream **160** descends, polymer **140** forms one or more solid polymeric fibers **165**. In the exemplary embodiment, fibers **165** are solid, however it should be noted that fibers **165** can have any structure including by not limited to, core or shell, porous, co-axial, and co-axial. Alternatively, polymer **140** deposition can be accomplished by any other fiber deposition method including but not limited to, solvent electrospinning, force electrospinning, melt electrospinning, extrusion, and melt blowing.

In some embodiments, a mask **164** composed of a conducting or non-conducting material is applied to collector **105** to manipulate deposition of fibers **165**. For example, mask **164** may be positioned between spinneret **120** and collector **105** such that no fibers **165** are deposited on collector **105** beneath mask **164**. Moreover, mask **164** may be used as a time-variant mask by adjusting its position between the spinneret and the collector while spinneret **120** dispenses polymer **140**, facilitating spatial variation of fiber density on collector **105**. While mask **164** is shown as circular, mask **164** may have any shape (e.g., rectangular or semi-circular) and size suitable for use with system **100**. Alternatively, or in addition, deposition of fibers **165** on collector **105** may be manipulated by adjusting the position of collector **105** with respect to spinneret **120** or by spatially varying the electrical potential applied between the spinneret **120** and/or the electrodes making up the collector **105**. For example, positioning one side of collector **105** directly beneath spinneret **120** may cause more fibers **165** to be deposited on that side than are deposited on the opposite side of collector **105** in a Gaussian distribution. To modulate the

spatial distribution of fibers forming on collector **105**, in some embodiments, a focusing device **138** is utilized to focus fiber deposition in a particular special region. In such an embodiment, focusing device **138** is charged with a polarity similar to spinneret **120** and includes an aperture allowing fiber deposition to occur substantially in the space under the aperture. Focusing device **138** may have any geometry that allows for receipt of nanofibers from spinneret **120** and deposition of the received nanofibers onto collector **105** as described herein.

FIG. **2** is a diagram of collector **105** removed from electrospinning system **100** (shown in FIG. **1**) and having a plurality of fibers **165** deposited thereon forming a patch **170**. Fibers **165** are oriented such that they correspond to the position of features **112** (shown in FIG. **1**).

Patch **170** is illustrated with a small quantity of fibers **165** in FIG. **2** for clarity. In some embodiments, patch **170** includes thousands, tens of thousands, hundreds of thousands, or more fibers **165**, distributed on collector **105**. Even with millions of fibers **165**, patch **170** retains predictable properties such as being flexible and/or pliable. As such, the predictable properties facilitate the application of patch **170** to uneven biological tissue surfaces, such as the surface of the dura mater.

The alignment of fibers **165** illustrates a patch **170** with varying densities. Patch **170** enables reinforcement or structural integrity to be provided in predetermined locations. For example, a larger deposition of fibers occurs in various locations, such as portion **167**, which provide structural reinforcement. Accordingly, system **100** enables the creation of customized materials **170** for individual biomedical or clinical and non-clinical applications.

In the exemplary embodiment, fibers **165** have a diameter of 1-3000 nanometers. In one embodiment, fibers have a diameter of approximately 220 nanometers (e.g., 215 nm to 225 nm). It should be noted that the diameter of the fibers **165**, thickness of the patch **170**, and/or fiber density within the patch **170** may affect the durability (e.g., tensile strength, suture pullout strength, conformability, etc.) of patch **170**. As such, the diameter of the fibers **165**, thickness of the patch **170**, and/or fiber density within the patch **170** can be selected according to the requirements of the end application of the material. Patch **170** may be produced with various mechanical properties by varying the thickness and/or the fiber density, spatial patterning, polymer composition, and/or number of layers of the patch **170** by operating electrospinning system **100** for relatively longer or shorter durations, changing the polymeric solution, changing the chemical composition, changing collector **105**, changing collector design, and/or changing the manner of fiber deposition.

FIG. **3** is an illustration **305** of a patch **170** including a plurality of electrospun fibers deposited on collector **105** and FIG. **4** is an illustration **405** of a patch **170** including a plurality of electrospun fibers deposited on collector **105**. In the exemplary embodiment, collectors **105** respectively provide an increased deposition of fibers on and substantial near features **112**. Such additional support and/or reinforcement properties are achieved by creating high density fiber deposition areas on charged features **112** and having low density fiber deposition areas over feature spaces **119**. It should be noted that collector **105** can include any pattern or combination of patterns such as the grid pattern shown in FIG. **3** and the hexagonal or honeycomb pattern shown in FIG. **4**.

Referring to FIGS. **1-4**, fibers **165** may be solid, core/shell, co-axial, or porous. In some embodiments, the size and/or structure of fibers **165** is determined by the design

and/or size of spinneret **120**, and/or polymer solution which includes viscosity, solvent or method of preparation of the solution, voltage or electric charge, distance between spinneret **120** and collector **105**, and rate of deposition. FIG. **5** is an illustration of a solid fiber spinneret **120A**. Solid fiber spinneret **120A** includes a truncated conical body **180** defining a center line **182**. At a dispensing end **184**, body **180** includes an annulus **186**. Annulus **186** defines a circular aperture **190A**, through which polymer **140** may be dispensed. Fibers **165** produced with solid fiber spinneret **120A** have a solid composition.

FIG. **6** is an illustration of a co-axial fiber spinneret **120B**. Like solid fiber spinneret **120A**, co-axial fiber spinneret **120B** includes a truncated conical body **180** with an annulus **186** at a dispensing end **184**. Co-axial fiber spinneret **120B** also includes a central body **188B** positioned within annulus **186**. Annulus **186** and central body **188B** define an annular aperture **190B**. Accordingly, when polymer **140** is dispensed by co-axial fiber spinneret **120B**, fibers **165** have a co-axial composition, with an exterior wall surrounding a cavity. The exterior wall of a fiber **165** dispensed by co-axial fiber spinneret **120B** defines an outer diameter corresponding to the inner diameter of annulus **186** and an inner diameter corresponding to the diameter of central body **188B**. Accordingly, the outer diameter and inner diameter of co-axial fibers **165** may be adjusted by adjusting the diameters of annulus **186** and central body **188B**.

Fiber spinnerets **120A** and **120B** facilitate incorporating a substance, such as a biological agent, growth factor, and/or a drug (e.g., a chemotherapeutic substance), into patch **170**. For example, the substance may be deposited within a cavity defined by co-axial fibers **165** of patch **170**. In one embodiment, polymer **140** is selected to create porous and/or semi-soluble fibers **165**, and the substance is dispensed from the cavity through fibers **165**. In another embodiment, polymer **140** is degradable, and the substance is dispensed as fibers **165** degrade in vivo. For example, fibers **165** may be configured to degrade within a second to 1 second to 12 months. In one embodiment, a burst release of the substance occurs upon entry into a system and an elution occurs over a predetermined period of time. The degradation rate of polymer **140** may be manipulated by any loading and/or release method such as adjusting a ratio of constituent polymers within polymer **140**, loading the agent into the bulk of the material, functionalizing the agent to the surface of the fibers, and/or releasing the agent by degradation of the polymer or by diffusion of the agent from the polymer. In another embodiment, a substance is delivered by solid fibers **165**. For example, a solid fiber **165** may be created from a polymer **140** including the substance in solution. As solid fiber **165** degrades, the substance is released into the surrounding tissue.

As shown in FIGS. **5** and **6**, annulus **186** is perpendicular to center line **182**. In an alternative embodiment, annulus **186** is oblique (e.g., oriented at an acute or obtuse angle) with respect to center line **182**. The outside diameter of fibers **165** may be determined by the inside diameter of annulus **186**.

FIG. **7** is an illustration of a multi-layer biomedical patch **435**. Patch **435** includes a biomedical patch layer with a plurality of symmetrical spatially organized fibers **420** and a biomedical patch layer with a plurality of spatially organized fibers having varying densities **425** such as increased density portions **430**. As shown in FIG. **7**, biomedical patch layers **420** and **425** are combined (e.g., fused, joined, adhered, overlaid) to produce multi-layer biomedical patch **435** with reinforcement fiber layers. It should be noted that any

combination, number, or type of fiber layers may be combined to create biomedical patch **435**. Combining the patches, especially layers **420** and **425**, facilitates providing a biomedical patch that promotes cell migration to a center of the biomedical patch while exhibiting potentially greater durability (e.g., tensile strength) than a biomedical patch having only standard, randomly-organized fibers. It should be noted that patch **435** can be formed of layers having various densities and/or thicknesses (both individually and collectively), fiber organizations, polymer compositions, surface coatings, and types of concentrations of agents and/or drugs.

In some embodiments, multiple biomedical patch layers **410-425** may be combined to create a multi-layer biomedical patch. For example, referring to FIGS. **1-4**, after depositing a first set of fibers on collector **105**, one may wait for the first set of fibers **165** to solidify completely or cure and then deposit a second set of fibers **165** on collector **105**. The second set of fibers **165** may be deposited directly over the first set of fibers **165** on collector **105**. Alternatively, the first set of fibers **165** may be removed from collector **105**, and the second set of fibers **165** may be deposited on conductive surface **162** and/or collector **105** and then removed and adhered/overlaid on the first set of fibers **165**. Such embodiments facilitate increased structural or mechanical reinforcement of the patch in predetermined locations, and added spatial control of cell migration/activity imparted by the layers 2-dimensionally and stacked layers 3-dimensionally. In some embodiments, a non nanofiber intermediate layer (e.g., hydrogel or polymeric scaffold) may be disposed between biomedical patch layers **400** and/or biomedical patch layers **410**.

In the exemplary embodiment, individual layers are fused or coupled together such that the layers delaminate or separate under specific environmental or temporal conditions. Such controlled delamination results in maximization of mechanical stability of the nanofiber material and the biological interaction (e.g. cellular ingrowth, tissue integration, cellular exposure, etc.) between adjacent layers of nanofibers. In the exemplary embodiment, the process of fusing or coupling layers includes, but is not limited to, heating, applying mechanical stress/pressure, applying an adhesive, chemical processing, cross-linking, and functionalization.

In one embodiment, adjacent layers are similarly or variably fused, adhered, or joined such that each layer delaminates or separates at a substantially similar rate within patch **435**. Alternatively, layers can be fused together with variable methods such that each layer delaminates at different rates. FIG. **8** illustrates delamination of patches **440**, **445**, and **450** with various fusion strengths over time. In the exemplary embodiment, a low strength adhesion **455**, such as but not limited to mild-chemical treatment or crosslinking, low-pressure physical lamination, or low-temperature thermal processing, is used to fuse layers of patch **440** together. Similarly, a moderate strength adhesion **460** such as but not limited to moderate chemical crosslinking, prolonged thermal processing, moderate mechanical entanglement, application of moderate adhesives, or high-pressure physical lamination is used to fuse the layers of patch **445** and a high strength adhesion **465**, such as but not limited to extensive chemical crosslinking, extensive high-temperature thermal processing, extensive mechanical entanglement, fiber interweaving or knitting, or application of aggressive adhesives is used to fuse layers of patch **450** together. In the exemplary embodiment, a separation **470** of patches **440**, **445**, and **450** is shown after a short increment of time, such

as, but not limited to 1 day-30 days and a separation **475** of patches **440**, **445**, and **450** is shown after a long increment of time, such as, but not limited to 30 days-3 years. As is shown, patch **440** is substantially separated **470** after a short period of time acting as an accelerated separation, patch **445** is substantially separated **475** after the long period of time acting as a delayed separation, and patch **450** provided substantially no separation.

FIGS. **9** and **10** are histological cross-sections **500** and **502** of dura mater repaired with multi-laminar nanofiber material such as patch **440** shown in FIG. **8**. Referring to FIG. **9**, patch **440** is shown as being inserted into dura **504** two weeks post-operatively. Regenerative dural tissue ("neodura") **504** is demonstrated extending on and around the implanted nanofiber material **440**. Regenerative dural fibroblasts are also shown to have penetrated the bulk of the nanofiber material **440**, demonstrating progressive cellularization of the implanted nanofiber construct. Two weeks following implantation of the multi-layer nanofiber material **440** no delamination is noted upon histological examination of the explanted tissue. The nanofiber material **440** is observed as a homogeneous block of material with low to moderate cellular ingrowth, yet no singular nanofiber layer or separation of nanofiber layers is observed. FIG. **10** illustrates controlled delamination of patch **440** six weeks post-operatively and integration of the patch within the native and/or regenerated dural tissue **504**. Regenerative dural tissue ("neodura") **504** is demonstrated extending on and around the implanted nanofiber material **440**. Additionally, regenerative dural tissue ("neodura") is demonstrated extending in between delaminated layers of the nanofiber material. Regenerative dural fibroblasts are shown to have significantly penetrated the bulk of the nanofiber material **440**, demonstrating robust cellularization and integration of the implanted nanofiber construct. Delamination of individual layers of nanofibers within the implant construct is noted upon histological examination of the explanted tissue. The nanofiber material **440** is observed as two heterogeneous layers of material separated by a thin layer of regenerated dural tissue extending along the adjoining surface of the nanofiber monolayers. Evidence of controlled delamination of the implanted material post-operatively is specifically demonstrated by observation that multiple layers of the material remain fused in proximity of sutures utilized to secure the material to the native tissue.

FIGS. **11** and **12** are histological cross-sections **506** and **508** of regenerated dura repaired with multi-laminar nanofiber material such as patch **450** shown in FIG. **8**. Referring to FIG. **11**, patch **450** is shown as being inserted into dura **504** two weeks post-operatively. Regenerative dural tissue ("neodura") **504** is demonstrated extending on and around the implanted nanofiber material **450**. Regenerative dural fibroblasts are also shown to have penetrated the bulk of the nanofiber material **450**, demonstrating cellularization of the implanted nanofiber construct. No delamination is noted upon histological examination of the explanted tissue. The nanofiber material **450** is observed as a homogeneous block of material with low to moderate cellular ingrowth, yet no singular nanofiber layer or separation of nanofiber layers is observed. FIG. **12** illustrates that the high strength adhesion has enabled layers of patch **450** to remain substantially fused together six week post-operatively as dural tissue **504** regenerated around patch **450**. Regenerative dural tissue ("neodura") **504** is again demonstrated extending on and around the implanted nanofiber material **450**. Dural fibroblasts substantially penetrate the bulk of the nanofiber material **450**, demonstrating robust cellularization of the implanted

11

nanofiber construct. Unlike nanofiber patch **440**, no delamination of nanofiber patch **450** is noted upon histological examination of the explanted tissue following chronic implantation. The nanofiber material **450** is observed as a secure composite material demonstrating cellular ingrowth yet no separation or observation of singular nanofiber layers.

FIG. **13** illustrates separation of layers within patches **600**, **602**, and **604** at varying rates. Each patch **600**, **602**, and **604** includes a first layer **606**, a second layer, **608**, a third layer **610**, and a fourth layer **612**. It should be noted that while patches **600**, **602**, and **604** are shown with four layers, patches can be fabricated to have any number of layers. Referring to patch **600**, low strength adhesion **455** is used to fuse layers **606**, **608**, and **610** together and high strength adhesion **465** is used to fuse layers **610** and **612** together. After a short time period, a separation **614** of layers **606**, **608**, and **610** has occurred and layers remain substantially fused together. As shown in patch **602**, moderate strength adhesion **460** is used to fuse together layers **606** and **608**, while high strength adhesion **465** is used to fuse together layers **608**, **610**, and **612**. A separation **616** of layers **606** and **608** occurs after a long period of time while substantially no separation occurs between layers **608**, **610**, and **612**. Referring to patch **604**, a high strength adhesion **465** is used between layers **606**, **608**, **610**, and **612** such that substantially no separation occurs between the layers.

A multi-layered biomedical patch may be useful for dural grafts as well as other tissue engineering applications. Sequential layers of fibers can be created with varying orders (e.g., radially aligned, reinforced, or randomly oriented), densities (e.g., low, high, or mixture of fiber density), patterns or reinforcement, and compositions (polymer), which may allow specific types of cells to infiltrate and populate select layers of the artificial biomedical patch. For example, biomedical patches containing a high fiber density generally prohibit cellular migration and infiltration, while biomedical patches containing a low fiber density generally enhance cellular migration and infiltration. Such additional support and/or reinforcement properties are achieved by creating high density fiber deposition that discourages cellular penetration and having low density fiber deposition areas that promote cellular penetration and/or ingrowth.

Overall, the ability to form multi-layered fiber materials, as described herein, may be extremely beneficial in the construction of biomedical patches designed to recapitulate the natural multi-laminar structure of not only dura mater, but also other biological tissues such as skin, heart valve leaflets, pericardium, and/or any other biological tissue. Furthermore, one or more layers of a biomedical patch may be fabricated from bioresorbable polymers such that the resulting nanofiber materials fully resorb following implantation. Manipulation of the chemical composition of the polymers utilized to fabricate these scaffolds may further allow for specific control of the rate of degradation and/or resorption of a biomedical patch following implantation.

FIG. **14** is a flowchart of an exemplary method **700** for producing a structure of spatially organized fibers using system **100** shown in FIG. **1**. While one embodiment of method **700** is shown in FIG. **14**, it is contemplated that any of the operations illustrated may be omitted and that the operations may be performed in a different order than is shown. In the exemplary embodiment, method **700** includes electrically charging **705** collector **105** at a first amplitude and/or polarity (e.g., negatively charging or grounding). Spinneret **120** is electrically charged **710** at a second amplitude and/or polarity opposite the first amplitude and/or polarity (e.g., positively charged). A polymer (e.g., a liquid

12

polymer) is dispensed **715** from spinneret **120**. In the exemplary embodiment, dispensed **715** polymers are collected **720** on collector **105** to form a plurality of polymeric fibers on or substantially near features **112** that creates a structure or patch. After the dispensed **615** polymers are collected **720** and a structure is created, the structure may undergo post-processing **725**. Such post-processing **725** can include, but is not limited to, lamination, layer stacking, coupling and/or fusing, chemically treating, and applying a biological agent, growth factor, and/or drug.

FIG. **15** is a flowchart of an exemplary method **750** for fusing or coupling together structures or patch layers produced by method **700** shown in FIG. **14**. Method **750** includes providing **755** a first, second, and third patch layer. First patch layer is coupled **760** to second patch layer using a first coupling technique. The coupled **760** first and second layers are then coupled **765** to the third patch layer using a second coupling technique different than the first coupling technique. In the exemplary embodiment, coupling techniques, include but are not limited to, heating, applying mechanical stress/pressure, chemical processing, cross-linking, and functionalization. While method **750** illustrates a first patch layer coupled to a second patch layer, it should be noted that multiple layers (e.g., 3, 5, 6) can be coupled together simultaneously. Additionally, the process may be repeated to add layers to structures produced by method **750**.

FIG. **16** is a flowchart of an exemplary method **800** for repairing a defect of a substrate using a structure produced by methods **700** and **750** shown in FIGS. **14** and **15**. In one embodiment, method **800** includes providing **805** a substrate substance with a defect. The defect may include a void, tissue defect, injury, insult, and/or any other condition resulting in diminished function of biological tissue. In the exemplary embodiment, the substrate is biological tissue. Alternatively, the substrate can be any substrate including but not limited to, filtration media, textiles, membrane media, and coatings. In one embodiment, the defect provided **805** includes a void created by surgical incision to provide access to an underlying tissue (e.g., a tumor). In another embodiment, a void is created **805** by excising necrotic tissue (e.g., skin cells). In the exemplary embodiment, one or more patches capable of covering the defect are selected **810**. For example, a plurality of biomedical patches may be selected **810** for a large and/or complex (e.g., irregularly shaped) defect. In the exemplary embodiment, a biomedical patch having a diameter greater than the diameter of an approximately circular defect is selected **810**. Alternatively, a patch is selected **810** and customized, pre-operation or intra-operation, to fit the defect. It should be noted that any size, shape, and/or geometry of structure may be used in the selection **810** of the patch.

In one embodiment, a substance such as a growth factor and/or a drug (e.g., a chemotherapeutic drug) is applied **815** to the biomedical patch. In the exemplary embodiment growth factor and/or a drug is applied **815** pre-operatively. However, it should be noted that growth factor and/or a drug may be applied **815** at any time including, but not limited to, intra-operatively and post-operatively. In one embodiment, the biomedical patch may be immersed in the substance to allow the substance to occupy a cavity within co-axial fibers of the biomedical patch, dope the polymer comprising the fibers in the biomedical patch, or coat the surface of the fibers within the biomedical patch.

In the exemplary embodiment, the patch is applied **820** to (e.g., overlaid on) the biological tissue to cover, repair, reinforce, and/or fill at least a portion of the defect. For example, the biomedical patch may be applied **820** to dura

13

mater tissue, cardiac tissue, and/or any biological tissue including a defect. In one embodiment, the perimeter of the biomedical patch extends past the perimeter of the defect, such that the entire defect is covered by the biomedical patch. In some embodiments, the biomedical patch is coupled **825** to the biological tissue with a plurality of sutures, adhesive, and/or any other means of attaching the biomedical patch to the biological tissue (inlay). In an alternative embodiment, the biomedical patch is simply allowed to fuse to the biological tissue, such as by adhesion of biological cells to the biomedical patch (onlay). In another embodiment, biomedical patch may be directly coupled to the edge of the tissue with no overlap. In one embodiment, biomedical patch may be overlaid on top of a wound/defect or injury covering the entirety of the defect or injury without filling the defect.

In one embodiment, after the biomedical patch is applied **820** and optionally coupled **825** to the biological tissue, the biological tissue is covered **830**. Alternatively, the patch may be the terminal covering. In such an embodiment, a backing that is either non-permeable or permeable may be coupled to the patch. In one embodiment, other tissue overlaying the defect (e.g., dermis and/or epidermis) is repaired (e.g., sutured closed). In another embodiment, one or more protective layers are applied over the biological tissue. For example, a bandage may be applied to a skin graft, with or without a protective substance, such as a gel, an ointment, and/or an antibacterial agent. In one embodiment, the protective layer includes, but is not limited to, a covering, film tissue, dressing, mesh, and nanofiber structure, such as an additional biomedical patch, as described herein.

Embodiments described herein are operable with any surgical procedure involving the repair, replacement, or expansion of the dura mater, including, but not limited to, a transphenoidal procedure (e.g., surgical removal of pituitary adenomas), various types of skull base surgeries, and/or surgical removal of cranial or spinal tumors (e.g., meningiomas and/or astrocytomas). In one embodiment, a biomedical patch may be applied to a bone fracture (e.g., a complex fracture). In another embodiment, a biomedical patch may be applied to a defect in the skin (e.g. a burn).

Moreover, such embodiments provide a dura mater substitute, a biomedical patch for a skin graft (e.g., dermal or epidermal), a biomedical patch for tracheal repair, a scaffold for an artificial heart valve leaflet, an artificial mesh for surgical repair of a gastrointestinal tract (e.g., an abdominal hernia or an ulcer), an artificial mesh for surgical repair of cardiac defects. Embodiments described herein facilitate providing a cardiac patch of sufficient flexibility to enable movement of the biomedical patch by a biological tissue (e.g., cardiomyocytes or cardiac tissue, muscle, skin, connective tissue, intestinal tissue, stomach tissue, bone, gastrointestinal tract, and mucosa).

In some embodiments, a biomedical patch has a thickness greater or less than a thickness of the biological tissue being repaired. Biomedical patches with spatially organized polymeric fibers facilitate reducing the expense of tissue repair, improving tissue healing time, and reducing or eliminating the risk of zoonotic infection. Moreover, such biomedical patches are relatively simple to manufacture, enabling customization of shape, size, and chemical composition and improved availability and non-immunogenicity. In addition, biomedical patches with spatially organized polymeric fibers exhibit excellent handling properties due to their cloth-like composition, eliminate the need for a second surgery to harvest autologous graft tissue, and reduce the risk of contracture and adhesion when compared with

14

known products. Additionally, the patches described herein facilitate reinforcement, buttressing, lamination, and/or sealing in a variety of applications such as but not limited to clinical and non-clinical applications.

Although the foregoing description contains many specifics, these should not be construed as limiting the scope of the present disclosure, but merely as providing illustrations of some of the presently preferred embodiments. Similarly, other embodiments of the invention may be devised which do not depart from the spirit or scope of the present invention. For example, while the illustrative examples have been used in with clinical applications, the above described nanofiber structures can have non-clinical application such as filtration, textiles, membrane technology, and coatings. Features from different embodiments may be employed in combination. The scope of the invention is, therefore, indicated and limited only by the appended claims and their legal equivalents, rather than by the foregoing description. All additions, deletions, and modifications to the invention as disclosed herein which fall within the meaning and scope of the claims are to be embraced thereby.

As used herein, an element or step recited in the singular and proceeded with the word “a” or “an” should be understood as not excluding plural elements or steps, unless such exclusion is explicitly recited. Furthermore, references to “one embodiment” of the present invention are not intended to be interpreted as excluding the existence of additional embodiments that also incorporate the recited features.

This written description uses examples to disclose various embodiments, which include the best mode, to enable any person skilled in the art to practice those embodiments, including making and using any devices or systems and performing any incorporated methods. The patentable scope is defined by the claims, and may include other examples that occur to those skilled in the art. Such other examples are intended to be within the scope of the claims if they have structural elements that do not differ from the literal language of the claims, or if they include equivalent structural elements with insubstantial differences from the literal languages of the claims.

What is claimed is:

1. A three-dimensional electrospun biomedical patch for facilitating tissue repair, the three-dimensional electrospun biomedical patch comprising:

- a first polymeric scaffold comprising a first structure of deposited electrospun fibers, the first structure of deposited electrospun fibers comprising a plurality of deposited electrospun fibers extending in a plurality of directions in three dimensions to facilitate cellular migration for a first period of time upon application of the three-dimensional electrospun biomedical patch to a tissue, wherein the first period of time is less than twelve months;
 - a second polymeric scaffold comprising a second structure of deposited electrospun fibers, the second polymeric scaffold overlaid on the first polymeric scaffold, the second polymeric scaffold comprising one or more portions with a higher deposition of fibers than one or more portions of the first polymeric scaffold, the second structure of deposited electrospun fibers comprising the plurality of deposited electrospun fibers configured to provide structural reinforcement for a second period of time upon application of the three-dimensional electrospun biomedical patch to the tissue, wherein the second period of time is less than twelve months;
- the plurality of deposited electrospun fibers connecting the first polymeric scaffold and the second polymeric

15

scaffold, the plurality of deposited electrospun fibers comprising a first set of deposited electrospun fibers generated by electrospinning a first polymer composition and a second set of deposited electrospun fibers generated by electrospinning a second polymer composition, wherein the first set of deposited electrospun fibers and the second set of deposited electrospun fibers are entangled; and

a plurality of voids, the plurality of voids comprising one or more voids between 10 μm and 10 cm,

wherein the three-dimensional electrospun biomedical patch is pliable and resistant to tearing to enable movement of the three-dimensional electrospun biomedical patch with the tissue.

2. The three-dimensional electrospun biomedical patch of claim 1, further comprising a spatial arrangement formed by one or more of the plurality of deposited electrospun fibers.

3. The three-dimensional electrospun biomedical patch of claim 2, wherein the spatial arrangement comprises an asymmetrical arrangement.

4. The three-dimensional electrospun biomedical patch of claim 2, wherein the spatial arrangement comprises a repeating pattern.

5. The three-dimensional electrospun biomedical patch of claim 2, wherein the spatial arrangement is formed by overlaying the second polymeric scaffold on the first polymeric scaffold.

6. The three-dimensional electrospun biomedical patch of claim 1, wherein the tissue comprises skin.

7. The three-dimensional electrospun biomedical patch of claim 1, wherein the tissue comprises one or more of skin, dura mater, heart valve leaflets, cardiac tissue, trachea, gastrointestinal tract, pericardium, muscle, connective tissue, intestinal tissue, stomach tissue, bone, gastrointestinal tract, or mucosa.

8. The three-dimensional electrospun biomedical patch of claim 1, wherein the first polymer composition comprises poly(lactic-co-glycolic acid).

9. The three-dimensional electrospun biomedical patch of claim 1, wherein the first polymer composition comprises glycolic acid, and wherein the second polymer composition comprises caprolactone.

10. The three-dimensional electrospun biomedical patch of claim 1, wherein the second polymeric scaffold is overlaid on the first polymeric scaffold by depositing the second structure of deposited electrospun fibers on the first structure of deposited electrospun fibers.

11. A three-dimensional electrospun biomedical patch for facilitating tissue repair, the three-dimensional electrospun biomedical patch comprising:

a first polymeric scaffold comprising a first structure of deposited electrospun fibers, the first structure of deposited electrospun fibers comprising a plurality of deposited electrospun fibers extending in a plurality of directions in three dimensions to facilitate cellular migration for a first period of time upon application of the three-dimensional electrospun biomedical patch to a tissue, wherein the first period of time is less than twelve months;

a second polymeric scaffold comprising a second structure of deposited electrospun fibers, the second polymeric scaffold overlaid on the first polymeric scaffold, the second polymeric scaffold comprising one or more portions with a higher deposition of fibers than one or more portions of the first polymeric scaffold, the second structure of deposited electrospun fibers comprising the plurality of deposited electrospun fibers configured to

16

provide structural reinforcement for a second period of time upon application of the three-dimensional electrospun biomedical patch to the tissue, wherein the second period of time is less than twelve months;

the plurality of deposited electrospun fibers connecting the first polymeric scaffold and the second polymeric scaffold, the plurality of deposited electrospun fibers comprising a first set of deposited electrospun fibers generated by electrospinning a first polymer composition and a second set of deposited electrospun fibers generated by electrospinning a second polymer composition, wherein the first set of deposited electrospun fibers and the second set of deposited electrospun fibers are entangled; and

a plurality of pores, the plurality of pores comprising one or more pores between 10 μm and 10 cm,

wherein the three-dimensional electrospun biomedical patch is pliable and resistant to tearing to enable movement of the three-dimensional electrospun biomedical patch with the tissue.

12. The three-dimensional electrospun biomedical patch of claim 11, further comprising a spatial arrangement formed by one or more of the plurality of deposited electrospun fibers.

13. The three-dimensional electrospun biomedical patch of claim 12, wherein the spatial arrangement comprises an asymmetrical arrangement.

14. The three-dimensional electrospun biomedical patch of claim 12, wherein the spatial arrangement comprises a repeating pattern.

15. The three-dimensional electrospun biomedical patch of claim 12, wherein the spatial arrangement comprises a symmetric arrangement.

16. The three-dimensional electrospun biomedical patch of claim 12, wherein the spatial arrangement is formed by overlaying the second polymeric scaffold on the first polymeric scaffold.

17. The three-dimensional electrospun biomedical patch of claim 11, wherein the tissue comprises skin.

18. The three-dimensional electrospun biomedical patch of claim 11, wherein the tissue comprises one or more of skin, dura mater, heart valve leaflets, cardiac tissue, trachea, gastrointestinal tract, pericardium, muscle, connective tissue, intestinal tissue, stomach tissue, bone, gastrointestinal tract, or mucosa.

19. The three-dimensional electrospun biomedical patch of claim 11, wherein the first polymer composition comprises poly(lactic-co-glycolic acid).

20. The three-dimensional electrospun biomedical patch of claim 11, wherein the first polymer composition comprises glycolic acid, and wherein the second polymer composition comprises caprolactone.

21. A three-dimensional electrospun biomedical patch for facilitating tissue repair, the three-dimensional electrospun biomedical patch comprising:

a first polymeric scaffold comprising a first structure of deposited electrospun fibers, the first structure of deposited electrospun fibers comprising a plurality of deposited electrospun fibers extending in a plurality of directions in three dimensions to facilitate cellular migration for a first period of time upon application of the three-dimensional electrospun biomedical patch to a tissue, wherein the first period of time is less than twelve months;

a second polymeric scaffold comprising a second structure of deposited electrospun fibers, the second polymeric scaffold overlaid on the first polymeric scaffold,

17

the second polymeric scaffold comprising one or more portions with a higher deposition of fibers than one or more portions of the first polymeric scaffold, the second structure of deposited electrospun fibers comprising the plurality of deposited electrospun fibers configured to provide structural reinforcement for a second period of time upon application of the three-dimensional electrospun biomedical patch to the tissue, wherein the second period of time is less than twelve months;

the plurality of deposited electrospun fibers connecting the first polymeric scaffold and the second polymeric scaffold, the plurality of deposited electrospun fibers comprising a first set of deposited electrospun fibers generated by electrospinning a first polymer composition and a second set of deposited electrospun fibers generated by electrospinning a second polymer composition, wherein the first set of deposited electrospun fibers and the second set of deposited electrospun fibers are entangled, wherein the plurality of deposited electrospun fibers are deposited in an arrangement comprising a plurality of pores between 10 μm and 10 cm; wherein the three-dimensional electrospun biomedical patch is pliable and resistant to tearing to enable movement of the three-dimensional electrospun biomedical patch with the tissue.

22. The three-dimensional electrospun biomedical patch of claim 21, further comprising a spatial arrangement formed by one or more of the plurality of deposited electrospun fibers.

18

23. The three-dimensional electrospun biomedical patch of claim 22, wherein the spatial arrangement comprises an asymmetrical arrangement.

24. The three-dimensional electrospun biomedical patch of claim 22, wherein the spatial arrangement comprises a repeating pattern.

25. The three-dimensional electrospun biomedical patch of claim 22, wherein the spatial arrangement comprises a symmetric pattern.

26. The three-dimensional electrospun biomedical patch of claim 22, wherein the spatial arrangement is formed by overlaying the second polymeric scaffold on the first polymeric scaffold.

27. The three-dimensional electrospun biomedical patch of claim 21, wherein the tissue comprises skin.

28. The three-dimensional electrospun biomedical patch of claim 21, wherein the tissue comprises one or more of skin, dura mater, heart valve leaflets, cardiac tissue, trachea, gastrointestinal tract, pericardium, muscle, connective tissue, intestinal tissue, stomach tissue, bone, gastrointestinal tract, or mucosa.

29. The three-dimensional electrospun biomedical patch of claim 21, wherein the first polymer composition comprises poly(lactic-co-glycolic acid).

30. The three-dimensional electrospun biomedical patch of claim 21, wherein the first polymer composition comprises glycolic acid, and wherein the second polymer composition comprises caprolactone.

* * * * *